

INDIGENOUS MATERIAL

(E) 16:10343 G. 40. OR BS: 3146 PE 1-74 TYPE CZA-S GRADE B'
-15: 10343 Gr. 40, CASTING TO BE HEAT-TREATED TO ACHIEVE 41.5-51.5 HRC
SEPARATULY CAST TEST BARS SHALL MEET THE SPECIFIED MECH. PROPERTIES
INCLUDING IZOD IMPACT VALUE 14J MIN.

BS: 3146: Pt.1: 1974, TYPE CLA-5 GRADE 'B'-

## RADIOGRAPHIC TEST

- (a) RADIOGRAPHIC ACCEPTANCE STANDARD OF THE CASTING SHOULD BE AS PER ASTM-E-192-Gr. A: (8)
- (b) 100% OF THE ADVANCE SAMPLE (NOT LESS THAN 5) WILL BE SUBJECTED TO RADIOGRAPHIC TEST.
- (c) RADIOGRAPHIC TEST OF ADVANCE SAMPLE WILL BE CARRIED OUT BY COA(MET) ICHAPUR.

OR

THE AREA QUALITY ASSURANCE OFFICER CONCERNED WOULD GET THE RADIOGRAPHIC TEST DONE IN HIS PRESENCE AND FORWARD THE PLATES TO -TO CQA (MET) ICHAPUR FOR SENTENCE AND APPROVAL OF THE MOULD.

- (d) BULK PRODUCTION WOULD COMMENCE ONLY AFTER MOULD AND MATERIAL HAS BEEN APPROVED BY CQA(MET) ICHAPUR.
- (e) 5% OF THE CASTING SELECTED AT RANDOM FROM BULK WOULD BE SUBJECTED TO RADIOGRAPHIC TEST. THIS MAY BE DONE UNDER THE ARRANGEMENT OF THE AREA QUALITY ASSURANCE OFFICER AND SENTENCE MAY BE AWARDED BY HIM BASED ON THE STANDARD OF THE ADVANCE SAMPLES CLEARED BY CQA(MET) ICHAPUR.

REF. ;- CONTROLLERATE OF QUALITY ASSU(W) JABALPUR LETTER NO. 50431/CQAIV/QA-11 DATED 14 MARCH 95.

EONTROLLERATE OF QUALITY ASSULT ICHAPUR
LEGITER NO. MICHA-3/LIN/3/W OL. 03 MAY 1995
INDIGENOUS MATERIAL: 15 10343 GY. 4E WITH CV. 0 45 - 0.50 AND MECHANICAL PROPERTIES SPECIFIED IN THE SPECIFICATION FOR THE GRADE
AUTHORITY: COA(METALS) ICHAPUR LY.NO. MQA-3/TS/B/J DE. 6/11-6-97

G) MATERIAL:

15: 10343 - 1999 Grade 19 Q WITH C% 0.45 - 0.5 P

DA: NO . 004/20 Dr. 30.06.20 Gr. 4. Added H (3) DA. NO. 001/16. DC. NO. 19446W 14.9.5 W 90 DA NO 052 97 FG) N 18 19 /2014 E(5) P 11/8/97 UPDATED. Dt - 23 - 3 - 97 DA. NO. 70/95 DA. 020/95 DE. 11-4-95 DO Saun < 3< 5 a d 41 DESCRIPTIONS SIG. & DATE

OF APPROVED DRAWINGS AT THIS DATE.....

17.11.2020

Ordnance Factory, Viruchirappalli-620014

UN CONTROLLED COPY

SHETS 2/2 APPROVED WAY MV. 12.4.95

Sad hi
DRAWN CHECKED 1/C.30mm D&DO

ORDNANCE FACTORY TIRUCHIRAPALLI

COMPONENT NO. 2A42-05-089 CATCHBOOY DRG. NO. 64C 5089 250 H3