

H-3

IS : 4228 - 1979

Indian Standard
SPECIFICATION FOR
NYLON TAPES FOR AEROSPACE PURPOSES
(*First Revision*)

UDC 677.754 : 677.494.675 : 629.13



CONTROLLED COPY

G. K. PRADHAN
Jr. WORKS MANAGER
ORDNANCE PARACHUTE FACTORY
KANPUR

© Copyright 1980

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Price Rs 5⁰⁰

3

March 1980

Indian Standard
SPECIFICATION FOR
NYLON TAPES FOR AEROSPACE PURPOSES
(First Revision)

Textile Materials for Aerospace Purposes Sectional Committee,
 TDC 27

Chairman

SHRI K. B. GANESAN

Representing

Directorate General of Civil Aviation, New Delhi

Members

SHRI P. R. CHANDRASEKHAR (<i>Alternate to</i> Shri K. B. Ganesan)	
SHRI M. K. BARDHAN	Ministry of Defence [DGI (CIT & C)]
SHRI K. K. KAPOOR (<i>Alternate</i>)	
SHRI M. S. EKBOTE	Indian Airlines, New Delhi
SHRI I. HUSSAIN	Ministry of Defence [R & D (ADRDE)]
SHRI S. K. GANGULI (<i>Alternate</i>)	
SHRI S. K. IVENGAR	J. K. Synthetics Ltd, Bombay
SHRI C. SIVARAMAN (<i>Alternate</i>)	
SHRI M. L. JAIN	Jaya Shree Textiles & Industries Ltd, Rishra
SHRI G. L. MOONDRA (<i>Alternate</i>)	
SHRI P. K. KURIAN	Hindustan Aeronautics Ltd, Bangalore
SHRI M. G. K. MURTHY	Ministry of Defence [DTD & P (Air)]
SHRI V. CHANDRASEKHARAN (<i>Alternate</i>)	
SHRI GAUTAMBHAI NANAVATY	Uttari Corporation, Ahmadabad
SHRI S. G. RATNAM	Madura Coats Ltd (Thread Group), Koratti
SHRI K. S. RAO (<i>Alternate</i>)	
REPRESENTATIVE	Ahmedabad Textile Industry's Research Association, Ahmadabad
SHRI G. H. RODRICKS	Fibreglass Pilkington Ltd, Bombay
SHRI G. RAVISHANKAR (<i>Alternate</i>)	
SHRI V. G. SARUKKAI	Acro Marine Industries Pvt Ltd, Madras
SHRI B. G. V. SUBRAHMANYAM	Indian Space Research Organization, Ahmadabad
SHRI M. G. THANAWALA	M. Best Cotton Rope Mfg Co, Bombay
SHRI P. G. THANAWALA (<i>Alternate</i>)	
SHRI S. B. TODI	Todi Industries Pvt Ltd, Bombay
SHRI N. B. TODI (<i>Alternate</i>)	

(*Continued on page 2*)

© Copyright 1980

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.



AMENDMENT NO. 1 JULY 1984

TO

IS: 4228-1979 SPECIFICATION FOR NYLON TAPES FOR
AEROSPACE PURPOSES

(First Revision)

Corrigendum

*(Page 4, clause 2.1, line 3) - Substitute '100'
for '10'.*

(TDC 27)

Reprography Unit, ISI, New Delhi, India

IS : 4228 - 1979

(Continued from page 1)

Members

SHRI R. VISWANATHAN
WG-CDE S. N. WADHWA

SHRI R. B. MOHINDRA (*Alternate*)

SHRI K. N. M. YELAHANKA

SHRI S. M. CHAKRABORTY,
Director (Tex)

Representing

Chemicals and Fibres of India Ltd, Thane
Ministry of Defence [Air HQ (Maintenance)]

Air India, Bombay

Director General, ISI (*Ex-officio Member*)

Secretary

SHRI S. M. AUROHA
Deputy Director (Tex), ISI

Indian Standard
SPECIFICATION FOR
NYLON TAPES FOR AEROSPACE PURPOSES
(*First Revision*)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 30 June 1979, after the draft finalized by the Textile Materials for Aerospace Purposes Sectional Committee had been approved by the Textile Division Council.

0.2 The tapes covered in the standard are used in the manufacture of various aerial delivery equipment including man-dropping parachutes.

0.3 This standard is based on IND/ADE/0603 'Tape, nylon, dyed/undyed' and IND/ADE/0072 'Tape, nylon, light, undyed/dyed', issued by the Ministry of Defence, Government of India.

0.4 This standard was first published in 1967. In this revision, 25.4-mm tape has been included at the instance of Chief Inspectorate of Textiles & Clothing, Kanpur.

0.5 To familiarize the industry with International System units (SI units), the basic as well as the recommended SI Units for use in the textile industry are given in Appendix A.

0.5.1 Standards of Weights and Measures Act, 1976 also stipulates use of SI Units.

0.6 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Rules for rounding off numerical values (*revised*).

1. SCOPE

1.1 This standard covers nylon tapes of 14, 19, 25, 32, 38, 44 and 25.4 mm width, generally used in the fabrication of parachutes and other aerial delivery equipment.

2. MATERIAL

2.1 Multifilament, bright and high tenacity nylon yarn of 23, 46 or 92 tex (as specified in the contract or order) shall be used in the manufacture of nylon tapes. The twist in the yarn shall not be less than 10 per metre both for warp and weft.

3. REQUIREMENTS

3.1 The nylon tapes shall meet the physical requirements given in Table 1.

3.2 The tapes shall further meet the chemical requirements given below:

<i>Characteristic</i>	<i>Requirement</i>	<i>Method of Test</i>
a) pH value	6.0 to 8.5	IS : 1390-1961*
b) Colour fastness to:		
1) light	5 or better	IS : 686-1957† or IS : 2454-1967‡
2) washing	No colour bleeding on white cotton/ white wool	IS : 764-1979§

3.2.1 The tapes shall be free from tendering substances.

3.2.2 *Dyed Tapes* — Acid/disperse dyes may be used; however, metallized/chrome dyes shall not be used [see IS : 4472 (Part III)-1973||].

3.3 The tapes shall be uniformly woven with firm and regular selvages in 2/2 herring bone twill weave with one reversal. They should be free from weaving defects and stains.

*Methods for determination of pH value of aqueous extracts of textile materials.

†Method for determination of colour fastness of textile materials to daylight.

‡Method for determination of colour fastness of textile materials to artificial light (xenon lamp).

§Method for determination of colour fastness of textile materials to washing: Test 3 (second revision).

||Methods for identification of application classes of dyes on textile materials: Part III Manmade fibres.

TABLE 1 PHYSICAL REQUIREMENTS OF NYLON TAPES

(Clause 3.1)

WIDTH, mm	LENGTH/ ROLL	THICK- NESS, mm	ENDS IN FULL WIDTH	PICKS/ dm	NO. OF PLYS		MASS, <i>Max</i>		BREAKING LOAD ON FULL WIDTH × 20 cm, <i>Min</i>		ELONG- ATION AT BREAK, PERCENT, <i>Min</i>
					Warp	Weft	g/m	g/66-m Roll (Net)	kN	kgf	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)
14 ± 1	66 m, unless otherwise specified in contract or order.	0.6 to 1.0	92 ± 5	134 ± 7	2	4	8.7	575	2.225	230	18
19 ± 1		0.5 to 0.8	150 ± 8	148 ± 7	1	2	6.2	410	1.895	193	18
25 ± 1		0.5 to 0.8	75 ± 4	134 ± 7	4	2	11.2	740	3.925	400	18
25.4 ± 1.6 (see Note)		0.25 to 0.75	104 ± 5	230 ± 12	1	1	4.5	295	1.345	137	14
32 ± 1		0.5 to 0.8	94 ± 5	134 ± 7	4	2	14.2	940	4.960	506	18
38.0 ± 1.5		0.5 to 0.8	112 ± 6	134 ± 7	4	2	16.8	1 110	5.935	605	18
44.0 ± 1.5		0.5 to 0.8	132 ± 7	134 ± 7	4	2	19.6	1 295	6.915	705	18
METHOD OF TEST	IS : 1954-1969*	IS : 7702- 1975†, under a pressure of 210 gf/cm ²	IS : 1963-1969‡	—	—	IS : 1964-1970§	IS : 1969-1968 , after con- ditioning the test speci- mens for 48 hours in standard atmosphere (65 ± 2 percent relative humidity and 27 ± 2°C temperature)				

NOTE — This is a special light variety with high cover factor.

*Methods for determination of length and width of fabrics (first revision).

†Method for determination of thickness of woven and knitted fabrics.

‡Methods for determination of threads per decimetre in woven fabrics (first revision).

§Methods for determination of weight per square metre and weight per linear metre of fabrics (first revision).

||Method for determination of breaking load and elongation at break of woven textile fabrics (first revision).

3.4 In respect of requirements not covered in this standard the tapes shall not be inferior to the sealed sample agreed to in the contract or order.

4. MARKING

4.1 Each roll shall bear a securely attached label with the following information:

- a) Name of the material and its net mass (g);
- b) Length (m), width (mm) and thickness (mm); and
- c) Name/trade-mark of the manufacturer and the year of manufacture.

4.1.1 Each roll may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

5. PACKING

5.1 An appropriate number of rolls shall be arranged in a cylindrical bundle and secured by jute twine to form a pack. A suitable number of such packs shall be arranged and wrapped with polyethylene film of at least 40 microns thickness (see IS : 2508-1978*) and placed in a wooden packing case of adequate strength, previously lined with one layer of waterproof packing paper conforming to Grade 2 of IS : 1398-1968†. The empty spaces, if any, in the packing case shall be stuffed with cushioning materials to avoid damage in transit. The case shall be bound by iron hoops or wires. The gross mass of the case shall not exceed 40 kg.

5.2 Each case shall be marked with the consignment details as provided in the contract or order in addition to the markings given in 4.1.

6. SAMPLING

6.1 **Lot** — The quantity of nylon tape of the same width in a consignment shall constitute a lot.

*Specification for low density polyethylene films (first revision).

†Specification for packing paper, waterproof, bitumen-laminated (first revision).

6.2 Unless otherwise specified in the contract or order, the sampling plan given in Table 2 shall be followed.

TABLE 2 SAMPLE SIZE AND CRITERIA FOR CONFORMITY
(Clauses 6.2 and 6.2.2)

LOT SIZE (NO. OF ROLLS)	SAMPLE SIZE (FOR LENGTH, WIDTH, MASS, THICKNESS, ENDS, PICKS AND PLYS)	PERMISSIBLE NO. OF DEFEC- TIVE ROLLS IN RESPECT OF TESTS ON SAMPLE ROLLS	SUB-SAMPLE SIZE (FOR BREAKING LOAD, ELONG- ATION, pH VALUE AND COLOUR FASTNESS)	PERMISSIBLE NO. OF DEFEC- TIVE ROLLS IN RESPECT OF TESTS ON SUB-SAMPLE ROLLS
(1)	(2)	(3)	(4)	(5)
Up to 25	3	0	3	None
25 " 100	5	0	4	
101 " 150	8	0	5	
151 " 300	13	0	7	
301 " 500	20	1	8	
501 " 1 000	50	1	9	
Above 1 000	80	2	10	

NOTE — ' Indian Standard sampling, inspection and testing scheme for aerospace materials ' is under preparation.

6.2.1 Rolls shall be selected at random.

6.2.2 Sub-sample rolls specified in col 4 of Table 2 shall be drawn from the sample rolls selected according to col 2 of the table.

6.2.3 For breaking load and elongation test, an additional 2-m test sample from each of the sample rolls remaining after drawing the sub-sample (see 6.2.2) shall be taken if so specified in the contract.

APPENDIX A

(Clause 0.5)

SI UNITS

TABLE 3 INTERNATIONAL SYSTEM UNITS

Base Units

QUANTITY	UNIT	SYMBOL
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

QUANTITY	UNIT	SYMBOL
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

QUANTITY	UNIT	SYMBOL	DEFINITION
Force	newton	N	1 N = 1 kg.m/s ²
Energy	joule	J	1 J = 1 N.m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V.s
Flux density	tesla	T	1 T = 1 Wb/m ²
Frequency	hertz	Hz	1 Hz = 1 c/s (s ⁻¹)
Electric conductance	siemens	S	1 S = 1 A/V
Electromotive force	volt	V	1 V = 1 W/A
Pressure, stress	pascal	Pa	1 Pa = 1 N/m ²

TABLE 4 RECOMMENDED SI UNITS FOR TEXTILES

Sl. No.	CHARACTERISTIC	SI UNITS		APPLICATION
		Unit(s)	Abbreviation(s)	
(1)	(2)	(3)	(4)	(5)
1)	Length	Millimetre Millimetre, centimetre Metre	mm mm, cm m	Fibres Samples, test specimens (as appropriate) Yarns, ropes, cordages, fabrics
2)	Width	Millimetre Centimetre Millimetre, centimetre Centimetre, metre	mm cm mm, cm cm, m	Narrow fabrics Other fabrics Samples, test specimen (as appropriate) Carpets, druggets, <i>DURRIES</i> (as appropriate)
3)	Thickness	Micrometre (micron) Millimetre	μm mm	Delicate fabrics Other fabrics, carpets, felts
4)	Linear density	Tex Millitex Decitex Kilotex	tex mtex dtx ktex	Yarns Fibres Filaments, filament yarns Slivers, ropes, cordages
5)	Diameter	Micrometre (micron) Millimetre	μm mm	Fibres Yarns, ropes, cordages
6)	Circumference	Millimetre	mm	Ropes, cordages
7)	Threads in fabric:			Woven fabrics (as appropriate)
	a) Lengthwise	Number per centimetre Number per decimetre	ends/cm ends/dm	
	b) Widthwise	Number per centimetre Number per decimetre	picks/cm picks/dm	
8)	Warp threads in loom	Number per centimetre	ends/cm	Reeds
9)	Stitches in the knitted fabric:			Knitted fabrics (as appropriate)
	a) Lengthwise	Courses per centimetre Courses per decimetre	courses/cm courses/dm	
	b) Widthwise	Wales per centimetre Wales per decimetre	wales/cm wales/dm	

(Continued)

TABLE 4 RECOMMENDED SI UNITS FOR TEXTILES — *Contd*

Sl. No.	CHARACTERISTIC	SI UNITS		APPLICATION
		Unit(s)	Abbreviation(s)	
(1)	(2)	(3)	(4)	(5)
10)	Stitch length	Millimetre	mm	Knitted fabrics Made-up fabrics
11)	Mass per unit area	Grams per square metre	g/m ²	Fabrics
12)	Mass per unit length	Grams per metre	g/m	Fabrics
13)	Twist	Turns per centimetre	turns/cm	} Yarns, ropes (as appropriate)
		Turns per metre	turns/m	
14)	Test or gauge length	Millimetre, centimetre	mm, cm	Fibre, yarns and fabric specimens (as appropriate)
15)	Breaking load	Millinewton	mN	Fibres, delicate yarns (individual or skeins) Strong yarns (individual or skeins), ropes, cordages, fabrics
		Newton	N	
16)	Breaking length	Kilometre	km	Yarns
17)	Tenacity	Millinewton per tex	mN/tex	Fibres, yarns (individual or skeins)
18)	Twist factor or twist multiplier	Turns per centimetre × square root of tex	turns/cm × √tex	} Yarns (as appropriate)
		Turns per metre × square root of tex	turns/m × √tex	
19)	Bursting strength	Newton per square centimetre	N/cm ²	Fabrics
20)	Tear strength	Millinewton	mN	Fabrics (as appropriate)
		Newton	N	
21)	Pile height	Millimetre	mm	Carpets
22)	Pile density	Mass of pile yarn in grams per square metre per millimetre pile height	g/m ² /mm pile height	Pile carpets
23)	Elastic modulus	Millinewton per tex per unit deformation	mN/tex/unit deformation	Fibres, yarns, strands