



**Technical Particulars for Webbing Nylon 19 mm, 2678 N (273 kgf) BS,  
Dyed/Undyed**


Sl. No.	Parameters	Specified Values	Test Method
1	Width, mm	19±1	IS: 1954
2	Thickness, mm, max (at 200 g/cm <sup>2</sup> Pressure)	0.89	IS: 7702
3	Mass, g/m, max	9.9	IS: 4727
4	Breaking Strength, N (kgf), min	2678(273)	IS: 1969
5	Extension at break, %, min	18	IS: 1969
6	Constructional Parameters i) Linear Density of Yarn, Tex [tolerance: (-)5% to (+)10%] Warp Weft ii) No. of ends in full width, min iii) Picks/dm, min	46.7×1 46.7×1 114+1ILT 270	IS: 3442 IS: 1963
7	Twist per meter (TPM), min Warp Weft	100 100	IS: 832
8	Weave	2/2 HBT, reversal at centre, 2 picks/shed	Visual
9	Material	Bright, High Tenacity, Multifilament, Nylon 6 or Nylon 66 Yarn	IS: 667/IS: 5762
10	Colour Fastness to Light*	5 or better	IS/ISO 105-B01 or IS/ISO 105-B02
11	Colour Fastness to Washing*	4 or better	IS/ISO 105-C10[Test Number A(1)]
12	pH Value	5.5 – 8.5	IS: 1390 Cold Method


\*: applicable for dyed varieties

**Note:** These technical particulars are tentative and these may undergo certain amendments during development, if required.

  
Sandeep Anand  
TO 'B'

  
Dev Kishan Bairwa  
Scientist 'B'

  
Prasanta Kumar Mallik  
Scientist 'E', DH, TG(TE)

  
Gaurav Singh  
Scientist 'F', GD, TG(TE)