

ANNEXURE –“C”
FOR BRACKET DRG.NO.2025460
(New Drg no. GCF/50/39490)

TECHNICAL REQUIREMENT OF CASTING Bearing Housing Blank Drg.No. 2025460
(New Drg. no. GCF/50/39490) AS PER SPECIFICATION – BOFORS STANDARD W3-2225-24 & NCTC
No.140-A TO SUPPLIED DULY HEAT TREATED AND RADIOGRAPHY QUALITY ASTM-E-446 LEVEL-2

1. METHOD OF MANUFACTURE

The castings shall be manufactured from electric arc furnace/ induction furnace aluminum killed steel through LOST FOAM casting Process only.

2. MATERIAL

2.1 Steel Grade: Specification BOFORS STANDARD W3-2225-24.

Or IS 10343:99, Gd 8Q Restricted %S & % P 0.035 %

2.2 Chemical Composition -

C%	0.22%-0.29%
Si%	0.30%-0.60%
Mn%	0.50%-0.80%
S%	0.035% Max
P%	0.035% Max
Cr%	0.90%-1.20%
Ni%	0.30%-Max
Mo%	0.15 -0.25%

2.3 Castings shall be free from any kind of casting defects such as blow holes, cracks, sand inclusion, shrinkage, pin holes, fins etc.

2.4 Permanent marking for Drg no, heat number, serial number. RG OK, should be punched on each casting at specified location in item drawing.

2.5 Iron oxide coating (except at the place of permanent marking).

3. HEAT TREATMENT

3.1 The castings are to be harden as per Heat treatment schedule no. OFM / TDS/ HTS Of item as per H-6 Hardening- heating to 650 Oc (Soaking -2 hours) and raised to 860-880⁰c (Soaking -2 hours) followed by Oil quenching

3.2 The castings are to be Tempering as per Heat treatment schedule no. OFM / TDS/ HTS Of item as per T-19 Tempering- - heating to 550 Oc (Soaking -4hours) and followed by Air cooling

3.3 HT should be carried out after clear the casting with Radiography Test Level-II .

3.4 Heat Treatment & SR graph will be required along with castings.

4. Mechanical properties:

4.1 Hardness : 235 -285 HB

4.2 Proof Stress (R_{po,2}) -600 N/mm²(min)

4.3 Ultimate Tensile strength (R_m) :-800-950 N/mm²

4.4 Elongation after fracture (Min) (A_s):-10 % on 5.65 under root 'A'

4.5 Reduction of Area (Z) :-25% Min

Body hardness of each and every casting is to be checked to ensure that prescribed hardness value is achieved.

Continue on page 2.....

5. **FETTLING**

5.1 Castings are to be fettled / well dressed.

5.2 During fettling, minor harmful defects are to be **weld** repaired if required & welding electrode used for minor weld repair shall be OK 73.08 of M/s Esab India Ltd. Mumbai (to be used before HT) **05**

6. **DIMENSIONAL & RADIOGRAPHY EXAMINATIONS.**

6.1 100% dimension checking required as per Drg. No. **Drg.No. 2025460** (New Drg. no. GCF/50/39490)

6.2 After dimension checking 100% casting to be **subjected** to radiographic test (Gamma rays) as per relevant RG standard ASTM-E 446-15 & acceptance **criteria** is RG level-2


6.3 After dimensional checking / radiography test, **Die Penetrate** (DP) test is required and if minor defects are observed on the surface, same can be **weld repaired** with specified welding electrode.


7. **DOCUMENTS & TEST CERTIFICATES:**


The supplier shall furnish following Test certificates /Reports along-with each supply

1. Hardness test report in the as supplied condition. (From NABL approved Lab.).
2. Chemical analysis report. (From NABL approved Lab.).
3. Radiography test report for 100% casting along with **R.G** film (From NABL approved Lab.).
4. 100 % dimension report through CMM.
5. All instruments and gauges for test & measurement **should** be calibrated .
6. Die penetrate test report 100% casting .
7. Challan Number.
8. HT & SR graph.

7. **Inspection Authority** : GENERAL MANAGER (OFM) or his authorized representative .


AGM /SN


WM/AK


HOS/LSF