



Technical Particulars for Webbing Nylon 25 mm, 11125 N (1134 kgf) BS, Dyed/Undyed


Sl. No.	Parameters	Specified Values	Test Method
1	Width, mm	25±1	IS: 1954
2	Thickness, mm, max (at 200 g/cm ² Pressure)	1.8	IS: 7702
3	Mass, g/m, max	33	IS: 4727
4	Breaking Strength, N (kgf), min	11125(1134)	IS: 1969
5	Extension at break, %, min	18	IS: 1969
6	Constructional Parameters i) Linear Density of Yarn, Tex [Tolerance: (-)5% to (+)10%] Warp	93.3×2 or 186.7×1 93.3×1 114+1ILT 120	IS: 3442
	Weft		
	ii) No. of ends in full width, min iii) Picks/dm, min		
7	Twist per meter (TPM), min Warp Weft	100 Nil/Manufacture's Twist	IS: 832
8	Weave	2/2 Herringbone Twill, 01 reversal at centre, 2 picks/shed	Visual
9	Material	Bright, High Tenacity, Multifilament, Nylon 6 or Nylon 66 Yarn	IS: 667/IS: 5762
10	Colour Fastness to Light*	5 or better	IS/ISO 105-B01 or IS/ISO 105-B02
11	Colour Fastness to Washing*	4 or better	IS/ISO 105-C10[Test Number A(1)]
12	pH Value	5.5 – 8.5	IS: 1390 Cold Method

*: applicable for dyed varieties

Note: These technical particulars are tentative and these may undergo certain amendments during development, if required.


Dev Kishan Bairwa
Sc 'C'


Gaurav Singh
Sc 'F', GD, TG(TE)


Prasanta Kumar Mallik
Sc 'E', DH, TG(TE)