



भारत सरकार
GOVERNMENT OF INDIA
रक्षा मंत्रालय
MINISTRY OF DEFENCE

संयुक्त सेवा विनिर्देश
JOINT SERVICES SPECIFICATION

ON

PAPER, WHITE FINE AMMUNITION
DCAN

(Paper, White Fine Ammunition 0.051 mm Thick - 9310-000 007)
(Paper, White Fine Ammunition 0.089 mm Thick - 9310-000 013)

मानकीकरण निदेशालय
रक्षा उत्पादन विभाग
रक्षा मंत्रालय
'एच'-ब्लॉक, निर्माण भवन डाकघर
नई दिल्ली-११००११

DIRECTORATE OF STANDARDISATION
DEPARTMENT OF DEFENCE PRODUCTION
MINISTRY OF DEFENCE
'H' BLOCK, NIRMAN BHAVAN POST OFFICE
NEW DELHI-110 011

LIST OF MEMBERS ASSOCIATED WITH FORMULATION OF THIS STANDARD

1. This Joint Services Specification has been approved by Shri RS Gauba, Sc 'G', Associate Director, PO-II, DRDO, Chairman, Armament Standardisation Sub-committee.
2. The representatives of following organisations have been present/consulted in approving the document:

S. No.	Organisations
1.	Programme Office-II, DRDO Orgn, New Delhi
2.	ADGWE/GS (WE-2/3), New Delhi
3.	Dte of Arty (GS/Artillery-5), New Delhi
4.	Dte Gen of Naval Armt, Naval HQ, New Delhi
5.	Dte of Armt & Safety Eqpt, Air HQ, New Delhi
6.	DGEME, Army HQ, New Delhi
7.	DGNAI, Naval HQ, New Delhi
8.	DGAQA, JD (Armt) Gp, New Delhi
9.	CQA (ME), Pune
10.	CQA (Amn), Pune
11.	CQA (SA), Ichapur, West Bengal
12.	CQA (W), Jabalpur
13.	HEMRL, DRDO, Pune
14.	ARDE/DRDO Orgn, Pune
15.	Ammunition Factory, Pune
16.	Secretary ASSC

RECORD OF AMENDMENTS

Amendment		Amendment pertains to S. No./Para No./ Column No.	Authority	Amended by	Signature & Date
No.	Date			Name & Appointment (In Block Letters)	

TABLE OF CONTENTS

S. No.	Topic	Page No.
0.	FOREWORD	1
1.	SCOPE	3
2.	RELATED SPECIFICATIONS/DOCUMENTS	3
3.	MATERIALS/MANUFACTURE	3
4.	TENDER SAMPLE	3
5.	PRE-INSPECTION OF STORES/CONSIGNMENT	3
6.	QUALITY ASSURANCE	4
7.	WARRANTY	5
8.	PACKAGING	5
9.	MARKING	6
10.	DEFENCE CATALOGUE NUMBER	6
11.	SAFETY OF OPERATIONS	6
12.	SUGGESTIONS FOR IMPROVEMENT	7

0. FOREWORD

0.1 This Joint Services Specification has been prepared by the Armament Standardisation Sub Committee on the authority of the Standardisation Committee, Ministry of Defence.

0.2 This specification has been approved by the Ministry of Defence and is mandatory for use by the Defence Services.

0.3 This JSS 9310-06 : 2016 (First Revision):

- a) was prepared in the year 2002.
- b) is a revision of JSS 9310-06 : 2002 Reaffirmed 2011 and supersedes the same.

0.4 This specification would be used for Manufacture, Quality Assurance and Supply of Paper, white fine ammunition.

0.5 Quality Assurance Authority for the item covered by this specification is the Controller, Controllerate of Quality Assurance (Military Explosives), Aundh Road, Pune-411 020. Enquiries regarding technical parameters shall be addressed to the Quality Assurance Authority, while other enquiries shall be referred to:

The Director,
Directorate of Standardisation,
Ministry of Defence,
'H' Block, Nirman Bhawan PO,
New Delhi-110 011.

0.6 Non-registered users can obtain the following on payment:

a) Copies of IS from:

Bureau of Indian Standards,
Manak Bhawan,
9, Bahadur Shah Zafar Marg,
New Delhi-110 002.

or

their regional/Branch offices.

b) Copies of JSSs/JSGs from:

The Director,
Directorate of Standardisation,
Standardisation Documents Centre,
Ministry of Defence,
Room No. 05, 'J' Block,
Nirman Bhawan PO,
New Delhi-110 011.

JSS 9310-06 : 2016
(First Revision)

0.7 Indian Standard (IS) specifications are available free of cost for registered users on:

Directorate of Standardisation Website:

www.ddpdos.gov.in

For registration visit our website.

0.8 This specification holds good only for the supply order for which it is issued.

0.9 Directorate of Standardisation Website - All the approved JSSs/JSGs are available on the Directorate of Standardisation Website *www.ddpdos.gov.in*. Defence Organisations desirous of accessing a copy of this document are requested to approach the Directorate of Standardisation for obtaining user ID/password to access the website.

1. SCOPE

1.1 This specification is meant to govern Manufacture, Supply and Quality Assurance of Paper, white fine ammunition suitable for use in ammunition components.

1.2 Paper, white fine ammunition to JSS 9310-06 for substance 84 g to 92 g per square metre is acceptable in lieu of paper, label, ammunition (colours required) to specification IND/ME/474 (a).

2. RELATED SPECIFICATIONS/DOCUMENTS

Reference is made in this specification to:

<i>S. No.</i>	<i>Specification/Document No. & Year</i>	<i>Nomenclature</i>
a)	IS 138 : 1992 (Third Revision) AMD 1 Reaffirmed 2014	Ready Mixed Paint, Marking, for Packages and Petrol Containers-Specification
b)	IS 1060 (Part 1) : 1966 (Revised) AMD 5 Reaffirmed 2014	Methods of Sampling and Test for Paper and Allied Products : Part 1
c)	IS 1060 (Part 2) : 1960 Reaffirmed 2014	Methods of Sampling and Test for Paper and Allied Products : Part 2
d)	JSG 0114 : 2015 (First Revision)	Methods of Tests for Textiles used in Ammunition
e)	IND/ME/474 (a)	Paper, Label, Ammunition (Colours Required)

3. MATERIALS/MANUFACTURE

3.1 The paper shall be made from pure bleached sulphite wood pulp. It shall be uniformly made. It shall be free from knots, lumps, cracks, pinholes or other defects. It shall be machine sized and one side glazed.

3.2 The paper shall be supplied in sheets or rolls of such size as may be prescribed by the terms of the contract.

4. TENDER SAMPLE

The manufacturer/contractor shall submit a tender sample of 500 g conforming to this specification, free of all charges. The sample shall be kept flat, preferably rolled without folds, wrinkles and protected from exposure.

5. PRE-INSPECTION OF STORES/CONSIGNMENT

5.1 Manufacturers/contractors must satisfy themselves that the stores are in accordance with the terms of contract and fully conform to the required specification, by carrying out a

JSS 9310-06 : 2016
(First Revision)

thorough pre-inspection of each lot before actually tendering the same for inspection to the Quality Assurance Officer nominated under the terms of the contract. A declaration by the contractor that a necessary pre-inspection has been carried out on the stores tendered will be submitted along with the challan. The declaration will also indicate the method followed in carrying out pre-inspection showing the features checked/tested and will have the test certificate attached to the challan/declaration.

5.2 If the Quality Assurance Officer finds that the pre-inspection of the consignment as required above has not been carried out, the consignment is liable for rejection.

6. QUALITY ASSURANCE

6.1 Inspection

6.1.1 The material shall be subjected to inspection by and to the final approval of the Quality Assurance Officer/Quality Assurance authority.

6.1.2 Samples of the material and of the packages may be taken from any portion of the batch/lot/consignment.

6.2 Sampling

6.2.1 Not less than five percent of the packages shall be sampled. Four representative sheets 250 g shall be taken from each package.

6.2.2 The samples from rolls shall not include the end metres and shall be cut with edges parallel to the machine and cross directions of the paper respectively.

6.3 Criteria for Conformity

6.3.1 If on examination, any sample is found not to conform to this specification, the whole batch/lot/consignment shall be rejected.

6.3.2 The foregoing provisions shall apply equally to prime contractors and sub-contractor, if any.

6.4 Test Requirements

Samples from any portion of batch/lot/consignment shall conform to Clause 3 above and in addition shall conform to the test requirements shown in the following tables:

a) *Chemical*

<i>S. No.</i>	<i>Characteristics</i>	<i>Passing Standard</i>	<i>Test Method</i>
1)	Moisture content at 103°C to 105°C for 2 h, % by mass	9.0 <i>Max</i>	IS 1060 (Part 1) Clause 9
2)	pH of aqueous extract	5.5 <i>Min</i> 7.5 <i>Max</i>	IS 1060 (Part 1) Clause 10
3)	Water soluble Chlorides calculated as Sodium chloride, % by mass	0.05 <i>Max</i>	JSG 0114 Method No. 5

(Concluded)

<i>S. No.</i>	<i>Characteristics</i>	<i>Passing Standard</i>	<i>Test Method</i>
4)	Water soluble Sulphates calculated as anhydrous Sodium Sulphate, % by mass	0.25 Max	IS 1060 (Part 2) Clause 18
5)	Fatty acids, calculated as Oleic acid, % by mass	0.25 Max	IS 1060 (Part 2) Clause 19
6)	The ash on incineration at 800°C ±25°C, % by mass	7.5 Max	IS 1060 (Part 1) Clause 11
7)	Lead (when Lead free material is required), calculated as metallic Lead, % by mass	0.03 Max	IS 1060 (Part 2) Clause 16

NOTE - All percent shall be calculated on the dry mass of the material after drying to a constant mass.

b) *Physical*

<i>S. No.</i>	<i>Characteristics</i>	<i>Passing Standard</i>	<i>Test Method</i>
1)	Substance, g/m ² i) 0.051 mm thick ii) 0.089 mm thick	42-46 84-92	IS 1060 (Part 1) Clause 6
2)	Thickness, mm i) 0.051 mm thick ii) 0.089 mm thick	0.051 ±0.005 0.089 ±0.009	IS 1060 (Part 1) Clause 7
3)	Bursting strength, kPa (average of at least 20 tests) i) 0.051 mm thick ii) 0.089 mm thick	110.8 179.4	IS 1060 (Part 1) Clause 12.6

NOTE - The material shall be conditioned prior to test, for 24 hours in an atmosphere of 65% ±2% relative humidity at 27°C ±2°C.

7. WARRANTY

The stores supplied against the contract shall be deemed to be warranted against the defective material and performance by the contractor for a period of 6 months from the date of receipt of the stores at the consignee's end and shall retain the properties described above. If during this period any of the stores supplied is found defective, the same shall be replaced by the manufacturer/supplier/contractor free of charges at the consignee's premises.

8. PACKAGING

8.1 The paper is to be delivered flat and unfolded in reams of 500 sheets. Each ream is to be wrapped in paper and 10 such reams are wrapped in hessian cloth to form a bale. The bale will be placed between two suitable thick boards (wood or paper) one on top and one at bottom, and the assembly bonded all round by hoop iron, for safe rail transit.

JSS 9310-06 : 2016
(First Revision)

8.2 When the supply is required in rolls, each roll is to be wrapped with packing paper followed by hessian and hoop ironed by bamboo strips.

or

Packaging (preservation and packing) should be in accordance with the terms of the contract.

9. MARKING

9.1 All packages containing the material shall indelibly and legibly be marked with the following details:

- a) Nomenclature and specification number of the material.
- b) Name and address of the consignee.
- c) A/T. or SO number and date.
- d) Consignment number.
- e) Batch No. and date of manufacture.
- f) Gross and net mass.
- g) Consecutive number of package and total number of packages in consignment.
- h) Date of supply.
- j) Manufacturer's initials or recognised trademark.

9.2 In addition to the above the Quality Assurance Officer may suggest some more markings/identifications suitable at the time of inspection.

9.3 The paint used for marking should conform to IS 138 (latest issue) and to the satisfaction of the Quality Assurance Officer/Quality Assurance Authority.

10. DEFENCE CATALOGUE NUMBER

The Defence Catalogue Number allotted to Paper, white fine ammunition are as under:

<i>S. No.</i>	<i>Nomenclature</i>	<i>DCAN</i>
a)	Paper, white fine ammunition 0.051 mm thick	9310-000 007
b)	Paper, white fine ammunition 0.089 mm thick	9310-000 013

11. SAFETY OF OPERATIONS

Nothing in this specification shall relieve the manufacturer/supplier/contractor of his responsibility for the safety of operations in the manufacture, storage, transit or use of this store.

12. SUGGESTIONS FOR IMPROVEMENT

Any suggestion for improvement in this specification shall be forwarded to:

The Director,
Directorate of Standardisation,
Ministry of Defence,
'H' Block, Nirman Bhawan PO,
New Delhi-110 011.