



DRG. No. GCF/50/41061

## FOR OTE (INDIGENISATION) ACTION ONLY

ALL DIMENSIONS ARE IN mm UNLESS OTHERWISE STATED



2	BOLT	SS 2541-03	ACC. TO NOTE	
1	RUBBER	POLYURETHANE	UNTREATED	$80 \pm 5^\circ$ ShA
NO.	DENOMINATION	MATERIAL	SURFACE TREATMENT	HARDNESS

P.No.	NOMENCLATURE		No. OFF	MATERIAL	HARDNESS	STANDARD	REMARKS
GEN. TOL. NOT SPECIFIED						<i>RF</i> FOR Sr. GM G.C.Fy.	
LINEAR DIMENSIONS						2022	NAME DATE
0-6 ±0.1						DRN.	AK 08/03
6-30 ±0.2						CKD.	
30-120 ±0.3							
120-315 ±0.5							
315-1000 ±0.8							
1000-2000 ±1.2							
ANGULAR DIMENSIONS	INDEX	AMENDMENTS		SIGN	DATE	APPROVED	<i>Approved</i>
0-10° ±1°							
10-50° ±30°							
50-100° ±20°							
>100° ±10°							
~ UNMACHINED							
▽ ROUGH							
▽▽ SMOOTH							
▽▽▽ FINISH							
	RUBBER BUFFER		GUN CARRIAGE FACTORY, JABALPUR		MATERIAL		
					SCALE REF.DRG.NO.		
					---		
					ASSY/SUB ASSY NO. 5177384		
					 DRG. No.GCF/50/41061		
					SHEET NO. OF SHEETS		

SURFACE TREATED — — — Y3-11-1

---

1

2

1

1

## GUN CARRIAGE FACTORY, JABALPUR

SHEET NO. OF SHEETS



Datum/ Date	Dok.nr/ Doc. No.
1985-01-15	38 008 543
Utgåva/ Issue	Sida/Page
2	1 (2)

AB BOFORS • STANDARD • BOX 600 • S-801 80 • BOFORS • SWEDEN • EFTERTRYCK UTAN SKRIFTLIG MEDGIVANDE FÖRBJUDS • COPYRIGHT

ZINKFOSFATERING DOPPNING	ZINC PHOSPHATING DIPPING
-----------------------------	-----------------------------

## 1 REFERENS

Motsvarar i vissa delar DOD-P-16232 type Z.

## 1 REFERENCE

Corresponds in some parts to DOD-P-16232 type Z.

## 2 OMFATTNING

Metoden är en kemisk ytbehandling av låglegerat stål varvid ett skikt av zink- och järnfosfat bildas på stålytan.

Den används även för varmförzinkade ytor som skall målas.

Legeringar med över 6 % koppar, kisel, krom och karbidbildare som krom, vanadin, molybden och volfram kan vara svåra eller möjliga att fosfatera.

Metoden omfattar 2 varianter

Y3-11 ..... Utan inoljning  
Y3-11-1 ..... Med inoljning

## 2 SCOPE

The method is a chemical treatment of low-alloy steel where a layer of zinc phosphate and iron phosphate are formed on the steel surface.

It is also used for hot dip galvanized surfaces which are to be painted.

Alloys with more than 6 % copper, silicon, chromium and carbide formers as chromium, vanadium, molybdenum and tungsten might be difficult or impossible to phosphatize.

The method includes 2 variants

Y3-11 ..... Without surface oiling  
Y3-11-1 ..... With surface oiling

## 3 ANVÄNDNINGSOMRÅDE

Y3-11 ..... Som underlag för målning  
Y3-11-1 ..... Som rostskyddsbehandling

## 3 RANGE OF APPLICATION

Y3-11 ..... As base for painting  
Y3-11-1 ..... As anti-rust treatment

## 4 FORDRINGAR

Fosfatskiktet skall ha utbildats på alla kravtyor och utgöras av ett finkristallint väl vidhäftande skikt. På härdade och slipade ytor kan grövre glittrande kristaller godtas.

## 4 REQUIREMENTS

The phosphate layer shall have been formed on all considered surfaces and consist of a fine-crystalline, well adhering layer. On hardened and ground surfaces coarser sparkling crystals can be accepted.

## 5 KOMPLETTERANDE UPPLYSNINGAR

Nedanstående egenskaper får inte anses bindande.

## 5 SUPPLEMENTARY INFORMATION

Properties given below must not be considered as binding.

### 5.1 Egenskaper

Skiktjäcklek ..... Upp till 8 µm beroende på legeringssammansättning, ytans beskaffenhet, eventuell härdning etc. Den verkliga mättförändringen är dock endast hälften eftersom ytan även betas under behandlingen

### 5.1 Properties

Thickness of layer ..... Up to 8 µm depending on alloy composition, the character of the surface, possible hardening etc. The real change of the measurements is not more than the half as the surface also is pickled during the treatment



Utgåva/Issue 2	Sida/Page 2
-------------------	----------------

Skiktets vikt .....	Upp till 10 g/m <sup>2</sup>	Weight of the layer .... Up to 10 g/m <sup>2</sup>
Spridningsförmåga .....	Fosfatskiktet utbildas på alla ytor som kommer i kontakt med badlösningen	Throwing power ..... The phosphate layer is formed on every surface been in contact with the bath liquid
Vidhäftning .....	God. Vid böjning av underlaget lossnar kristallerna vid bokningsstället	Adhesion ..... Good. At bending the base material the crystals at the bending place will come loose
Utseende .....	Grått, kristallint skikt	Appearance ..... Grey, crystalline layer
Nötningsbeständighet ..	Kristallskiktet deformeras lätt	Abrasion resistance .... The crystal layer is easily deformed
Elektriska egenskaper ..	Skiktet kan vara elektriskt isolerande	Electrical properties .. The layer can be electrically insulating
Värmebeständighet .....	God upp till 150 °C	Heat resistance ..... Good up to 150 °C
Korrosionsbeständighet		Corrosion resistance
Y3-11 .....	Mindre god	Y3-11 ..... Poor
Y3-11-1 .....	God	Y3-11-1 ..... Good

## 5.2 Identifiering

## 5.2 Identification

Metodnummer Method number	Benämning Denomination	Beteckning Designation
11 500 144	Zinkfosfatering Zinc phosphat.	Y3-11
11 500 145	Zinkfosfatering Zinc phosphat.	Y3-11-1

Intern verkstads  
anvisning

V8-4

Internal workshop  
description

V8-4