

2.3.2.4 Dibutyl phthalate (TU 32 E-2015)

As related to physical and chemical parameters, dibutyl phthalate shall comply with the requirements specified in Table 5.

Table 5

| Parameter | Standard value for grades | | |
|--|--|-------------|--------------|
| | Premium grade | First grade | Second grade |
| Exterior view | Transparent liquid without mechanical impurities | | |
| Colority by the platinum-cobalt scale, Hazen units, max. | 50 | 80 | 200 |
| Density at 20 °C, g/cm ³ | 1.045–1.049 | | |
| Acid value, mg of KOH/g, max. | 0.07 | 0.07 | 0.10 |
| Saponification value, mg of KOH/g | 399–407 | | |
| Flash point, °C, min. | 168 | 168 | 168 |
| Weight ratio of volatile matters, %, max. | 0.3 | 0.3 | — |

Skudz

DGM/mm

M

.Tw m/m,