

COLD-ROLLED SHEET STEEL.

GOST 19904-74

ASSORTMENT.

SUPERSIDES \*

SIT 1 OF 14

**COPY-8**

**FOR REFERENCE ONLY.  
WILL NOT BE KEPT AMENDED**

\* GOST 3596-57, GOST 3075-56  
in the part of sheets of thickness 0.5 mm and more and GOST 3630-57 in the part of cold-rolled sheets.

1. This standard pertains to cold-rolled sheet-steel of width 500 mm and more, fabricated in sheets of thickness from 0.5 to 5.0 mm and in rolls having thickness from 0.5 to 3.0 mm.

In the standard the requirements of the recommendation of SEV as per standardization PS 440-71 are taken into account.

2. Dimensions of steel, fabricated in sheets, should correspond to data in table No.1 and that into rolled - in table No. 2.

steel

3. Sheet/roll is subdivided into:

a) as per accuracy of rolling:

high accuracy - A;

standard accuracy - B;

b) as per planeness:

extra high planeness - PO;

high planeness - PV;

improved planeness - PU.

APPROVED			MATL/SPECN.			
ENGINEER / CH. INCHARGE			HEAT TREAT			
CHECKED			FINISH			
DRAWN				ISS. NO.	ISSD. BY	APPRD.

standard planeness - PN;

c) according to the type of edge:

with non-cut edge - NO;

with cut edge - O;

d) according to dimensions:

with indication of dimensions on thickness, width and length in conformity with dimensions, shown in appendix - form I;

with indication of dimensions on thickness in the limits, shown in table No. 1, without indication of dimensions on width and length - form II;

Contd. . . . /-

COLD-ROLLED SHEET STEEL ASSIGNMENT

Table 1.

Thickness of sheets, mm	Minimum and maximum length of sheets at width, mm																								
	500	550	600	650	700	710	750	800	850	900	950	1000	1100	1250	1400	1500	1600	1700	1800	2000	2100	2200	2300		
1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26
0.50	1000 2500	1100 2500	1200 2500	1300 2500	1400 2500	1400 2500	1500 2500	1500 2500	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000	1500 3000
0.55	1000	1100	1200	1300	1400	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500
0.60	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500
0.65																									
0.70	1000	1100	1200	1300	1400	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500
0.75	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500
0.80																									
0.90	1000	1100	1200	1300	1400	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500
1.00	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000
1.1	1000	1100	1200	1300	1400	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500
1.2	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000
1.3																									
1.4																									
1.5	1000	1100	1200	1300	1400	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500
1.6	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000
1.7																									
1.8																									
2.0																									
2.2	1000	1100	1200	1300	1400	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500	1500
2.5	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000

Continued

COLD-ROLLED SHEET STEEL ASSORTMENT

	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	245	26
2.8;	1000	1100	1200	1300	1400	1500	1500	1500	1500	1500	1500	1500	1500	1500	2000	2000	2000	2000	2000	2500	2500	2500	2500	2500	2500	2500
3.0;	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	3000	4000	4000	6000	6000	6000	6000	6000	2750	2700	2700	2700	2700	2700	2700
3.2															2000	2000	2000	2000	2000	2500	2500	2500	2500	2500	2500	2500
3.5;															1500	4500	4500	4750	2750	2750	2700	2700	2700	2700	2700	2700
3.8;															2000	2000	2000	2000	1500	1500	1500	1500	1500	1500	1500	1500
3.9															4500	4500	4500	4500	2500	2500	2500	2500	2500	2500	2500	2500
4.0															2000	2000	2000	2000	1500	1500	1500	1500	1500	1500	1500	1500
4.2															4500	4500	4500	4500	2300	2300	2300	2300	2300	2300	2300	2300
4.5															2000	2000	2000	2000	1500	1500	1500	1500	1500	1500	1500	1500
4.8															4500	4500	4500	4500	2300	2300	2300	2300	2300	2300	2300	2300
5.0																										

Note: According to the agreement between customer and manufacturer sheets of other dimensions can be supplied.

Table 2.

Width of steel	Thickness of steel supplied, in rolls.																				
	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00										
500	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
530	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
550	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
570	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
600	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
630	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
650	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
670	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
700	0.50;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
(710)	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
750	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
800	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
850	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
900	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
950	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
1000	0.5;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00
1100	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00;	3.00;
1250;	0.55;	0.60;	0.65;	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	3.00;	3.00;
1400	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	2.80;	3.00;			
(1420)	0.70;	0.75;	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	2.80;	3.00;			
1500	0.80;	0.90;	1.00;	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	2.80;	3.00;					
1600	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	2.80;	3.00;								
1700	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.70;	1.80;	2.00;	2.20;	2.50;	2.80;	3.00;								
1800	1.10;	1.20;	1.30;	1.40;	1.50;	1.60;	1.80;	2.00;	2.20;	2.50;	2.80;	3.00;									
1900	2.20;	2.50;																			
2000	2.20;	2.50;																			
2100	2.20;	2.50;																			
2200	2.20;	2.50;																			
2300	2.20;	2.50;																			

Note: According to agreement between the parties rolled steel can be supplied with other thickness and width in comparison with the data in table No. 2.

Table 3.

Maximum deviations for thickness at width of steel (sheets and rolls)

Thickness of steel (sheets and rolls)	From 500 to 750				Above 750 to 1000				Above 1000 to 1500				Above 1500 to 2000				Above 2000 to 2300			
	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling	High accuracy of rolling	Standard accuracy of rolling		
0.50	+0.04	+0.05	+0.04	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05	+0.05		
0.55	+0.05	+0.06	+0.05	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06	+0.06		
0.60	+0.05	+0.07	+0.06	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08	+0.08		
0.70	+0.07	+0.09	+0.08	+0.10	+0.09	+0.10	+0.09	+0.10	+0.09	+0.10	+0.09	+0.10	+0.09	+0.10	+0.09	+0.10	+0.09	+0.10		
0.80	+0.08	+0.10	+0.09	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10	+0.10		
0.90	+0.09	+0.11	+0.10	+0.12	+0.11	+0.12	+0.11	+0.12	+0.11	+0.12	+0.11	+0.12	+0.11	+0.12	+0.11	+0.12	+0.11	+0.12		
1.00	+0.11	+0.13	+0.12	+0.14	+0.12	+0.14	+0.12	+0.14	+0.12	+0.14	+0.12	+0.14	+0.12	+0.14	+0.12	+0.14	+0.12	+0.14		
1.10	+0.12	+0.14	+0.13	+0.15	+0.13	+0.15	+0.13	+0.15	+0.13	+0.15	+0.13	+0.15	+0.13	+0.15	+0.13	+0.15	+0.13	+0.15		
1.20	+0.14	+0.16	+0.15	+0.17	+0.15	+0.17	+0.15	+0.17	+0.15	+0.17	+0.15	+0.17	+0.15	+0.17	+0.15	+0.17	+0.15	+0.17		
1.30	+0.15	+0.17	+0.16	+0.18	+0.16	+0.18	+0.16	+0.18	+0.16	+0.18	+0.16	+0.18	+0.16	+0.18	+0.16	+0.18	+0.16	+0.18		
1.40	+0.16	+0.18	+0.17	+0.19	+0.17	+0.19	+0.17	+0.19	+0.17	+0.19	+0.17	+0.19	+0.17	+0.19	+0.17	+0.19	+0.17	+0.19		
1.50	+0.16	+0.18	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19		
1.60	+0.16	+0.18	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19	+0.18	+0.19		
1.70	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
1.80	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
1.90	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.00	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.10	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.20	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.30	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.40	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.50	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.60	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.70	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.80	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
2.90	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.00	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.10	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.20	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.30	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.40	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.50	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.60	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.70	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.80	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
3.90	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		
4.00	+0.18	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20	+0.19	+0.20		

Note: According to the requirement of the undertaking of Ministry for aviation industry supply of sheet steel with negative tolerances equal to the value of total maximum deviations is allowed.

with indication of dimensions, multiple in width and length dimensions shown in the order, in the limits, fixed in table 1 - form III;

with indication of measured dimensions in the limits, shown in table No. 1 with intervals of 10 mm for width and 50 mm for length - form IV.

According to agreement between customer and manufacturer intervals for width and length can be less than those mentioned.

Supply of sheet steel of measured dimensions which differ from dimensions shown in the appendix is carried out according to the requirement of customer.

Tolerances on thickness of steel, supplied in sheets and rolls should not exceed the norm specified in table No. 3, at any point of measuring.

5. According to the requirement of customer difference in thickness of steel in transverse section should not exceed half the total tolerances on thickness.

6. Tolerances on width of steel with cut edge supplied in rolls should not exceed:

+ 2 mm - at width from 500 to 1000 mm;

+ 5 mm - at width above 1000 to 1600 mm;

+ 7 mm - at width above 1600 mm.

7. Tolerances on width of steel with cut edge, supplied in sheets, should not exceed:

+ 6 mm - at width upto 800 mm;

+ 10 mm - at width above 800 mm.

8. Tolerances on width of steel with non-cut edge should not exceed  $\pm 20$  mm.

9. Tolerances on length of sheet steel, rolled sheet-wise, should not exceed:

- + 10 mm - at length of sheets upto 1500 mm;
- + 15 mm - at length of sheets above 1500 mm.

10. Tolerances on length of sheet steel, rolled on continuous rolling mill and cut into sheets, should not exceed:

- + 15 mm - at length of sheets upto 1500 mm;
- + 20 mm - at length of sheets above 1500 to 3000 mm;
- + 25 mm - at length of sheets above 3000 mm.

11. Deviations from planeness for 1 m length of steel, supplied in sheets, should not exceed the norm shown in table No. 4.

12. Crescent shapeness of steel, supplied in rolls, should not exceed 10 mm on a length of 3 m.

On agreement between customer and manufacturer other values of crescent shapeness can be fixed.

13. Steel which is to be supplied in sheets with cut edge should be cut into right angles. Slope of cut and crescent shapeness should not lead the sheets beyond nominal dimension.

Table No. 4.

Types of planeness	Deviations from planeness when width of steel is			
	Upto 1000	Above 1000 upto 1500	Above 1500 upto 1800	Above 1800
Extra high	4	5	6	8
High	8	8	10	10
Improved	10	12	15	15
Standard	12	15	18	20

Notes:

1. Deviations from planeness, given in table No. 4 pertain to sheets made from steel with  $\delta_1 \leq 70 \text{ kgf/mm}^2$ , for sheets made from sheet with  $\delta_1 > 70 \text{ kgf/mm}^2$  the norms are specified in the standards on general technical requirements or in the technical specifications.
2. Sheet steel with extra high planeness is supplied according to the agreement between the parties.
14. While supplying steel in sheets and rolls with non-cut edge tears and other defects (in case they are present on the edges) should not exceed half the tolerances on width and should not lead the sheets beyond the nominal dimension of width shown in the order.
15. Steel, supplied in rolls, should not have wasted and piled ends. In individual places bent edges at angle not more than  $90^\circ$  is allowed.
16. Telescopicity of steel, supplied in rolls, should not exceed the norm indicated in table No. 5.

Table No. 5.

Thickness of steel	Width of steel	Telescopicity of rolls
Upto 2.5	Upto 800	40
	Above 800	75
Above 2.5	Upto 800	30
	Above 800	50

Increase of one internal or one external turn over the surface of the end of roll is not telescopicity.

Uneven adjoining of two external turns of rolls is not rejection reason.

17. Thickness of steel is measured in the following way:

a) on sheets - at distance not less than 100 mm from faces and 40 mm from edges;

b) on rolls - at distance not less than 40 mm from the edges and 2 m from the edge of roll.

18. Width of steel, supplied in rolls, is measured at a distance not less than 2 m from the edge of roll.

19. Deviation from planeness of steel, supplied in sheets, is determined from maximum deflection between the sheet surface, laid on the plane surface, and a meter scale placed on it in any direction.

20. Steel, supplied in rolls, can consist of not more than two pieces (individual or combined welded seam).

Ratio of lengths of pieces in one roll should not be less than 1:5.

On agreement between the parties supply of rolls with more quantity of pieces or welded seams is allowed.

21. Internal diameter of steel, supplied in rolls, should not be less than 500 mm and not more than 1000 mm.

22. Maximum weight of steel, supplied in rolls, should not exceed 20 t.

According to agreement between customer and manufacturer, supply of steel in rolls of other weight is allowed.





