

48

ADRDE/SPECN/68

RAKSHA MANTRALAYA  
MINISTRY OF DEFENCE

PROVISIONAL SPECIFICATION  
FOR  
**TAPE NYLON TUBULAR BRAIDED**  
1.5 cm 800 kgf DYED /UNDYED

ISSUED BY  
DIRECTOR / NIDESHAK  
HAWAI VITRAN ANUSANDHAN AVAM VIKAS SANSTHAPAN  
RAKSHA MANTRALAYA

AERIAL DELIVERY RESEARCH AND DEVELOPMENT ESTT.  
MINISTRY OF DEFENCE  
POST BOX NO. 51  
STATION ROAD  
AGRA CANTT - 282 001

Ref: - ADRDE/GMS/MAT/94 dt. 24/09/13.

RECORD OF AMENDMENTS

Amendment No.	Sub heading to which amendment pertains	Authority	Incorporated by Name & Rank in Block letters	Initials
---------------	---	-----------	--	----------

<b>CONTENT</b>	<b>PAGE No.</b>
0. FOREWORD	4
1. SCOPE	6
2. RELATED SPECIFICATIONS	6
3. REFERENCE STANDARD	8
4. MATERIAL	8
5. MANUFACTURE	9
6. FINISH	10
7. REQUIREMENTS	10
8. MARKING	12
9. QUALITY	12
10. PRE INSPECTION OF STORES/CONSIGNMENT	12
11. SAMPLING	13
12. CRITERIA FOR CONFORMITY	16
13. INSPECTION	17
14. WARRANTY	17
15. PACKAGING	17
16. DEFENCE STORES CATALOGUE NUMBER	19
17. SUGGESTION FOR IMPROVEMENT	20
18. APPENDIX 'A'	21
19. APPENDIX 'B'	22

**TAPE NYLON TUBULAR BRAIDED 1.5 cm 800 kgf DYED / UNDYED**

0. **FOREWORD**

0.1 This specification is the revision of provisional specification No. ADDE/BP/1/ (b) for item at sl. no. 7. It has now been revised on the basis of the problem faced and experience gained during production and use.

0.2 The revised specification has been prepared by a special committee of ADRDE and approved by the Director, ADRDE, Agra

0.3 This specification would be used for manufacture, inspection and procurement of Tape Nylon Braided Tubular 1.5 cm 800 kg Dyed / Undyed against Defence requirements.

0.4 In case of any discrepancy between this specification and any sample or pattern, this specification shall be taken as correct

- 0.5 Enquiries regarding this specification in relation to any contractual conditions should be addressed to the Inspection Authority named in tender or contract. Other enquiries will be referred to the issuing authority, Director, ADRDE, Agra.
- 0.6 Whenever a reference to any other specification occurs in this specification, it shall be taken as a reference to the latest version of that specification.
- 0.7 Copies of this specification can be obtained on payment from :
- i. The Director,  
A.D.R. & D.E.,  
P.B. No. 51, Station Road,  
Agra Cantt. - 282 001
  - ii. Concerned Inspectors and Inspection Authority.
- 0.8 IS specifications quoted in this specification may be obtained directly from B.I.S., Manak Bhawan, 9, Bahadur Shah Zafar Marg, New Delhi - 110 002 or its offices located in the country.

1. **SCOPE**

- 1.1 This specification covers the requirement of Tape Nylon Tubular Braided 1.5 cm 800 kgf Dyed / Undyed used in the manufacture of parachutes B.P. can also be used in other aerial delivery application considering the suitability.

2. **RELATED SPECIFICATIONS**

- 2.1 Reference is made in this specification to :

- i. IS:2 Rules for rounding off numerical values.
- ii. IS:6359 Methods for conditioning of textiles.
- iii. IS:1954 Methods for determination of length and width of fabrics.
- iv. IS:7702 Method for determination of thickness of woven and knitted fabrics.

- vi. IS:4727 Method for determination of weight per (App.'A') metre.
- ✓ vii. IS:1969 Methods for determination of breaking load and elongation at break of woven textile fabrics.
- ✓ viii. IS:3442 Determination of crimp and count of yarn removed from fabric.
- ✓ ix. IS:832 Method for determination of twist in yarn.
- x. IS:1390 Method for determination of pH value of aqueous extracts of Textiles (cold method).
- xi. IS:2454 Method for determination of colour fastness of textile materials to artificial light (Xenon lamp).
- xii. IS:3361 Method for determination of colour fastness of textile materials to washing (test 2).
- xiii. IS: 5762 Methods for determination of melting temperature and melting range.
- ✓ xiv. IS:7151 Specification for corrugated fibre board boxes for para dropping of supplies.

- xv IS:9738 Polythene bags.
- xvi IS:5762 Methods for the determination of melting temperature/ range.

2.2 All specifications referred to in this specification for any tender or contract, shall mean the current edition on the date of such tender or contract.

3. REFERENCE STANDARD

3.1 The standard of the tapes, held by ADRDE, Agra Cantt, shall constitute the reference standard as regards any particulars of properties not noted/defined in this specification.

4. MATERIAL

4.1 The basic material shall be of nylon 66, high tenacity, multifilament, bright yarn suitably twisted as per Appendix 'A' to meet the requirements stipulated at clause 7. **One spool of about 200 metre of the basic yarn material along with its test results should be supplied by the firm for testing/approval before starting the production of Advance sample (Ref. Clause 5.2).**

5. MANUFACTURE

- 5.1 Nylon yarn used in the manufacture of the tape shall be of Du Pont or its equivalent standard manufactures' product that will ensure the compliance of the tape with the requirement of this standard.
- 5.2 The tape shall be evenly braided under suitable tension. The tension given to the yarn during braiding shall be intimated along with the processing/manufacturing details. **A piece of ten metre sample along with the test results shall be forwarded as an advance sample for approval.**
- 5.3 The tape shall not be more than one year old from the date of manufacture to the date of delivery. A certificate to this effect shall be provided by the manufacturer/contractor at the time of delivery.

**6. FINISH**

6.1 The tape shall be suitably heat set (if required) under already approved conditions of temperature, pressure and time. The supplier should primarily get approved the sequence of processes to achieve the specified properties.

6.2 The tape shall have minimum braiding defects. The tape when laid on a flat even surface, shall be in a straight line without application of any tension. For detail classification of defects, appendix 'B' of this specification may be consulted.

**7. REQUIREMENTS**

7.1 The tape shall conform to the particulars given in appendix 'A', when tested in accordance with the methods mentioned in Related Specifications under clause 2.

7.2 pH Value : pH value of the finished tape shall be within the range of 5.5 to 8.5, when tested as per the relevant method.

- 7.3 Colour fastness to light : Colour fastness to light of the finished tape shall be five or better when tested as per the relevant method.
- 7.4 Colour fastness to washing : Colour fastness to washing of the finished tape shall be four or better when tested as per the relevant method.
- 7.5 Melting Temperature: The melting temperature of nylon yarn used in the manufacture of the tape shall be  $250\pm 6^{\circ}\text{C}$ . When determined as per relevant method.
- 7.6 Sealed Sample : If, in order to illustrate or specify the unmeasurable characteristics like general appearance, feel, etc of the tape, sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.
- 7.6.1 The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

8. **MARKING**

- 8.1 Each piece, prior to being offered for inspection, shall legibly be marked by the supplier with his name, initials or recognized trade mark, the year of manufacture, brief nomenclature, DS Cat. number of the store and length of the piece along with the number of flags contained in the piece.

9. **QUALITY**

- 9.1 On examination of sample taken from any portion of consignment, shall show that the tape conforms to the requirements of clause 7 above.

10. **PRE-INSEPTION OF STORES/CONSIGNMNET**

- 10.1 Manufacturers / contractors must satisfy themselves that the store is in accordance with the terms of the contract and fully conforms to the required specification by carrying out a thorough pre-inspection of each lot before actually tendering the

same for inspection to the inspecting officer nominated under the terms of the contract. A declaration by the contractor that necessary pre-inspection has been carried out on the store tendered, will be submitted along with the challan. The declaration will also indicate the method followed in carrying out pre-inspection showing the features checked/tested and will have the test certificate attached to the challan/declaration.

- 10.2 If the Inspecting officer finds that pre-inspection of the consignment as required above has not been carried out, the consignment is liable for rejection.

11. **SAMPLING**

- 11.1 The manufacturer / supplier shall tender store duly numbered and arranged in such a way that all the units are easily accessible to the Inspector.

- 11.2 The samples shall be drawn lot wise for carrying out tests specified in this specification. Unless otherwise agreed to between the buyer and the seller, the lot shall be defined

under respective sampling plans as detailed below. The tape shall be in continuous length without joints of not less than 100 m or its multiple or as agreed between the buyer and the seller.

However, shorter cuts may be allowed in accordance with the following schedule or as agreed between the buyer and the seller:-

90 % of the total supply in length of 100 m

10 % of the total supply in length of 50 m or above

11.3 **SAMPLING PLAN 'A'**

11.3.1 **LOT** - The total length of the tape manufactured from same type of yarn purchased from the same supplier/ manufacturer and of same braiding construction and finish, delivered to a buyer against one dispatch note shall constitute a lot.

11.3.2 Each ball/hank of the lot shall be measured for its length.

11.3.3 One sample of three metre length and of full width shall be drawn from each ball / hank of the lot for carrying out the **Breaking load and Extension at break**

11.4 **SAMPLING PLAN 'B'**

11.4.1 LOT - All the ball / hank of tape manufactured from same type of yarn purchased from the same supplier / manufacturer and of same braiding construction and finish, delivered to a buyer against one dispatch note shall constitute a lot.

11.4.2 Five samples or 10 % of the lot, whichever is more, shall be drawn for the following tests. Each sample shall be of five metre length and of full width :

- a) Width
- b) Thickness
- c) Mass

11.5 **SAMPLING PLAN 'C'**

11.5.1 LOT - The quantity of tape manufactured from the same

type of yarn purchased from the same supplier / manufacturer and of the same braiding construction and finish, delivered to a buyer against one despatch note shall constitute a lot.

11.5.2 Two samples or 2 % of the lot, whichever is more, should be drawn for the following tests; each sample shall be of two metre length and of full width :

- a) Braiding construction
- b) Plaits /dm
- c) Linear density of yarn
- d) pH value
- e) Colour fastness to light
- f) Colour fastness to washing
- g) Type of basic material
- h) Twist of yarn
- i) Melting temperature of yarn

## 12 CRITERIA FOR CONFORMITY

12.1 All the sample units drawn as per clause 11.2 above, shall be tested/examined to the relevant requirement / specification. The lot shall be considered to be in conformity if the requirements given in clause 7 are satisfied.

13. **INSPECTION**

- 13.1 If, on examination, 20 percent of those examined, are found not to conform to this specification in any respect, the whole consignment may be rejected.

14. **WARRANTY**

- 14.1 The store supplied, shall be deemed to bear a warranty of the contractor against defective material, poor workmanship and performance for a period of twelve months from the date of receipt of the store at consignee's depot.

- 14.2 If, during the period, the store supplied is found by the consignee to be defective, the same shall be replaced immediately with serviceable store by the contractor at site, free of any charge or cost.

15. **PACKAGING**

- 15.1 Each ball / hank shall be wrapped with polythene bag as per IS:9738 and secured by line cotton (0.32 cm) to

form a unit pack. Suitable number of such unit packs shall then be wrapped with paper craft wrapping and placed in corrugated fibre board box as per IS 7151 of suitable size provided with line water proof bag. The gross mass of the box shall not exceed 40 kg. The empty spaces if any shall be filled in with cushioning material to prevent any movement of the contents inside the corrugated fibre board box and the top lid of box shall be properly fixed with adhesive tape. The box packing shall be made secured by fastening with suitable tapes/cords.

15.2 Packing material used, should be approved by Inspecting Officer. If ordered for delivery to a local inspection depot, the store shall be delivered in the same fashion as stated above in cl no. 15.1. After inspection, the accepted supplies shall be packed by the inspection depot concerned as indicated in para. 15.1 above.

15.3 Before despatch, each box of corrugated fibre board packing, shall be legibly and indelibly marked, showing following details :

- a) Nomenclature and D S Cat number.
- b) Quantity packed in each corrugated fibre board box.
- c) Serial no. of the corrugated fibre board box.
- d) Month and year of packing.
- e) Name and trade mark of the manufacturer.
- f) Gross mass of each corrugated fibre board box  
in Kg.
- g) Name and address of the consignee.
- h) Inspection Note number and date.

16. **DEFENCE STORES CATALOGUE NUMBER**

16.1 Not yet allotted.

17. SUGGESTION FOR IMPROVEMENT

17.1 Any suggestion for improvement of this document may be forwarded to the Director, ADRDE, Agra Cantt - 282 001.

Place : Agra Cantt

Date : 30<sup>th</sup> Jan. 2004

*spah*  
Head / Q A C  
For DIRECTOR  
ADRDE, Agra Cantt

## APPENDIX 'A'

Width, mm	Thickness, under 200g/cm <sup>2</sup> pressure, max, mm	Mass, max, g/m	Breaking Load min., kgf	Extension at break, %	Construction	Linear Density of twisted yarn (with a tolerance of 3 to + 8 %), tex.
(1)	(2)	(3)	(4)	(5)	(6)	(7)
14 - 16	2.2	17.0	800	25-35	Braided	140 X 1 <sub>9</sub>

Note - In case of dyed tape, 5 % relaxation shall be allowed in mass per unit  
Length and extension at break.

Total no. of ends in full width	Plaits per dm	Twist of yarn (with a tolerance of 15 %)
(8)	(9)	(10)
96 (2 ends / spindle)	55±3	100

## APPENDIX 'B'

**CLASSIFICATION OF DEFECTS**

1. The following defects found in metre by metre examination are classified as major / minor.

**Major/minor defects detectable visually during inspection**

Defects	Description	Major	Minor
Abrasion	Abrasion resulting in broken filaments, rupture of individual yarn	X	
Broken and missing threads	Any broken and protruding thread from the surface of the cord	X	
	Any missing thread	X	
Coarse or light ends	Over one end 0.10 m, long	X	
	Over two ends	X	
	Two ends over .05m long	X	
	One end 0.1m. long		X
	Two ends 0.05m. long		X

Double end	Two or more additional ends along full length	X	
	One additional end along full length		X
Slack end	Two or more for a minimum of 13 mm in length	X	
	Two or more for less than 13 mm in length		X
Kinks	Any kink	X	
Loops, snarles, Slack or loose ends(per 10 linear metre)	Over 1	X	
	Over 2 metre	X	
	2 m maximum		X
	Only one		X
Knots or Plied yarns	Over 1 knot in plied yarn	X	
	One knot in plied yarns		X
Light place pull down, step marks or uneven plaits	Over 5 cm	X	
	Upto 5 cm		X

Tight ends	Over 1 end 0.25 m long	X	
	Two or more tight ends	X	
	One end 0.25 m long		X
Spot, stain	Single thread 40 cm or more in length	X	
	Single thread upto 40 cm. Or less in length		X
	Double threads 20 cm or more in length	X	
	Double threads upto 20 cm or less in length		X
	Over two threads 12 cm or more in length	X	
	Over two threads less than 12 cm. in length		X
Smash	Any smash	X	
Wrong Draw	Extending for more than 25 cm	X	
	Extending upto 25 cm.		X

2. **Acceptance of hanks / balls with defects**

2.1 Each hank / ball shall be visually examined for defects as described in clause 1 above . No hank / ball shall contain more than 5 major defects per 100 m or 18 minor defects per 100 m. For this purpose, all the hanks / balls shall be visually examined metre by metre and the defects classified in accordance with clause 1 above . The unit of product for examination, shall be one linear metre. For each unit of product, the defects shall be counted as follow:

- i) One major defect and one minor defect shall be counted as one major defect.
- ii) Three or more minor defects shall be counted as one major defect.
- iii) A continuous major defect shall be counted as one major defect for each unit of product or fraction thereof in which it occurs.

2.2 Each major defect shall be flagged by a red string. Each minor defect shall be flagged by a blue string. Three or more minor defects occurring per linear metre shall be flagged by a red string.