

IS : 70 - 1980
(Reaffirmed 2009)
(Reaffirmed 2014)
(Reaffirmed 2019)

Indian Standard

**SPECIFICATION FOR
CUPROUS OXIDE FOR PAINTS**

(First Revision)

First Reprint MAY 2000

UDC 661.856.22:667.6

© *Copyright* 1980

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Gr 4

June 1980

AMENDMENT NO. 1 SEPTEMBER 1987

TO

**IS:70-1980 SPECIFICATION FOR CUPROUS OXIDE
FOR PAINTS**

(First Revision)

(Page 4, Table 1, Sl No. (iii), col 3] –
Substitute ' $\pm 10'$ for $\pm 5'$).

(CDC 50)

AMENDMENT NO. 2 NOVEMBER 1993
TO
IS 70 : 1980 SPECIFICATION FOR CUPROUS OXIDE
FOR PAINTS
(*First Revision*)

(*Page 4, clause 3.1*) — Add a new sub-clause after it:

'**3.1.1** The total copper shall not be less than 85 percent, by mass, when tested as prescribed in Appendix E.'

(*Page 12, Appendix D*) — Add a new Appendix after it:

'APPENDIX E
(*Clause 3.1.1*)

DETERMINATION OF TOTAL COPPER

E-1 PRINCIPLE OF THE METHOD

E-1.1 Copper is determined by titration of the iodine liberated on addition of potassium iodide to the weakly acidic solution. Difficulties with absorption of iodine on the cuprous iodide precipitate are avoided by the addition of potassium or ammonium thiocyanate.

E-2 REAGENTS

E-2.1 Concentrated Nitric Acid — sp gr 1.42 (*see* IS 264 : 1968).

E-2.2 Urea

E-2.3 Sodium Carbonate — anhydrous (*see* IS 296 : 1965).

E-2.4 Dilute Acetic Acid — 10 percent (*v/v*).

E-2.5 Potassium Iodide Solution — 30 percent (*m/v*).

E-2.4 Standard Sodium Thiosulphate Solution — 0.1 N, standardized against pure copper or against 0.1 N standard potassium dichromate solution (*see* E-5).

E-2.7 Starch Indicator Solution — One percent (*m/v*), freshly prepared.

E-2.8 Potassium or Ammonium Thiocyanate

E-3 Procedure

E-3.1 Weigh accurately about 0.4 g of the material into a 250-ml Erlenmeyer flask. Add 1 to 2 ml of concentrated nitric acid and about 20 ml of water, and allow the material to dissolve by shaking. Boil the contents for 3 to 5 minutes, remove the flask from the flame, add 1 g of urea and boil again for about 5 minutes. Cool and add sodium carbonate in small quantities until a faint permanent precipitate or blue colour appears. Add dilute acetic acid dropwise until the blue colour (or the precipitate) disappears. Add 2 to 3 ml of potassium iodide solution and titrate the brown solution with the standard sodium thiosulphate solution to a pale-straw colour. Add about 2 ml of starch indicator solution and about 1.5 to 2.5 g of potassium or ammonium thiocyanate, and continue titration until the blue colour is just discharged.

E-4 CALCULATION

$$\text{E-4.1} \quad \begin{array}{l} \text{Total copper content,} \\ \text{percent by mass} \end{array} = \frac{0.6357 \nu F}{M} \times 10$$

where

ν = volume in ml of the standard sodium thiosulphate solution required for the test with the material (see E-3.1),

F = factor of the standard sodium thiosulphate solution (see E-5.1.2.1 and E-5.2.3.1), and

M = mass in g of the material taken for the test (see E-3.1).

E-5 STANDARDIZATION OF SODIUM THIOSULPHATE SOLUTION

E-5.0 General — For standardization of sodium thiosulphate solution, two methods, namely titration against pure copper of not less than 99.9 percent purity and against standard potassium dichromate solution, have been specified. Experience has shown that the standardization against pure copper gives accurate results but due to difficulty of availability of pure copper, the alternate method has also been specified. Hence, either of these two methods may be used for the standardization of sodium thiosulphate solution, but the method employed should be stated while expressing the results of a test.

E-5.1 Standardization Against Pure Copper of not less than 99.9 Percent Purity

E-5.1.1 Weigh accurately 0.2 g of pure copper in a 500-ml Erlenmeyer flask. Dissolve the copper by adding 5 ml of concentrated nitric acid and, after 1 minute, add 5 ml of water. Follow the procedure as described in **A-3.1**.

E-5.1.2 Calculation

E-5.1.2.1 Factor F of 0.1 N sodium thiosulphate solution =
$$\frac{M}{0.6357v}$$

where

M = mass in g of the pure copper taken for the test, and

v = volume in ml of the standard sodium thiosulphate solution required for the test with the material.

E-5.2 Standardization Against Standard Potassium Dichromate Solution

E-5.2.1 Reagents

E-5.2.1.1 *Standard potassium dichromate solution* — 0.1 N.

E-5.2.1.2 *Concentrated hydrochloric acid* — conforming to IS:265-1962.

E-5.2.1.3 *Potassium iodide*

E-5.2.1.4 *Starch Indicator solution* — one percent (m/v), freshly prepared.

E-5.2.2 Calculation

E-5.2.2.1 Pipette out accurately 25 ml of standard potassium dichromate solution into a 600-ml Erlenmeyer flask. Add to this about 125 ml of water, 10 ml of concentrated hydrochloric acid and 4 to 5 g of potassium iodide. Stopper the Erlenmeyer flask and keep it in dark for about 15 minutes to complete the reaction. After 15 minutes, titrate this mixture against the standard sodium thiosulphate solution using about 2 ml of starch indicator solution towards the end.

E-5.2.3 Calculation

$$\text{E-5.13.1 Factor F of 0.1 N sodium thiosulphate solution} = \frac{VN}{v}$$

where

V = volume in ml of the standard potassium dichromate solution taken for the test (which in this case is equal to 25 ml),

N = normality of the standard potassium dichromate solution, and

v = volume in ml of the 0.1 N sodium thiosulphate solution required for titration of the volume of the standard potassium dichromate solution taken for the test.'

(CHD 021)

IS : 70 - 1980

Indian Standard

SPECIFICATION FOR CUPROUS OXIDE FOR PAINTS

(First Revision)

Raw Materials for Paint Industry Sectional Committee, CDC 50

<i>Chairman</i>	<i>Representing</i>
DR R. J. RATHI	Sudarshan Chemical Industries Ltd, Pune
<i>Members</i>	
SHRI K. L. RATHI (<i>Alternate to Dr R. J. Rathi</i>)	Indian Paint Association, Calcutta
SHRI S. G. ARCHICK DR P. K. BHANDARI (<i>Alternate</i>)	Ministry of Defence (DGI)
SHRI S. K. ASTHANA SHRI S. S. KATIYAR (<i>Alternate</i>)	State Trading Corporation of India Ltd, New Delhi
SHRI K. J. BHATT SHRI S. MURGAN (<i>Alternate</i>)	Alkali and Chemical Corporation of India Ltd,
SHRI S. BHATTACHARYYA	
SHRI M. L. MALHOTRA (<i>Alternate</i>)	Asian Paints (India) Ltd, Bombay
SHRI C. J. BHUMKAR CHEMIST & METALLURGIST-II, RDSO	Railway Board, Ministry of Railways
ASSISTANT RESEARCH OFFICER-II, RDSO (<i>Alternate</i>)	
SHRI G. C. DESAI	Goodlass Nerolac Paints Ltd, Bombay
SHRI M. R. NAIR (<i>Alternate</i>)	Garware Paints Ltd, Bombay
SHRI S. H. DESAI SHRI R. R. SEQUEIRA (<i>Alternate</i>)	Export Inspection Council Ltd, Calcutta
SHRI O. P. DHAMIJA SHRI S. N. DATTA (<i>Alternate</i>)	Directorate General of Technical Development, New Delhi
SHRI R. D. KAWATRA	
SHRI KULTAR SINGH (<i>Alternate</i>)	Oil Technologists' Association of India, Kanpur
SHRI A. S. KHANNA SHRI T. K. S. MANI SHRI M. B. SATYANARAYANA	Addisons Paints & Chemicals Ltd, Madras (<i>Alternate</i>)
SHRI D. L. MEHTA SHRI V. M. NACHANE DR S. D. YADAV (<i>Alternate</i>)	Hindustan Petroleum Corporation Ltd, Bombay Chowgule & Co (Hind) Ltd, Bombay

(Continued on page 2)

© Copyright 1980

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 70 - 1980

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI V. C. PANCHAMIYA	Kamani Metallic Oxides Pvt Ltd, Bombay
SHRI B. RAMAMURTI	Travancore Titanium Products Ltd, Trivandrum
DR V. S. VIJAYAN NAIR (<i>Alternate</i>)	Ministry of Defence (R&D)
DR G. K. SINGHANIA	Ministry of Defence (R&D)
SHRI I. K. LOOMBA (<i>Alternate</i>)	Development Commissioner, Small Scale Industries, New Delhi
SIIRI P. SATYANARAYANAN	Development Commissioner, Small Scale Industries, New Delhi
SHRI K. C. SEAL	National Test House, Calcutta
SHRI R. M. TILLU	Colour-Chem Ltd, Bombay
SHRI M. E. MARATHE (<i>Alternate</i>)	Indian Dyestuff Industries Ltd, Bombay
SHRI M. VAITHYANATHAN	Indian Dyestuff Industries Ltd, Bombay
SHRI V. R. KARMAKAR (<i>Alternate</i>)	Director General, ISI (<i>Ex-officio Member</i>)
DR G. M. SAXENA, Director (Chem)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary

SHRI R. K. SINGH

Deputy Director (Chem), ISI

Pigments and Extenders Subcommittee, CDC 50 : 1

Convener

SHRI K. C. SEAL National Test House, Calcutta

Members

SHRI S. K. ASTHANA	Ministry of Defence (DGI)
SHRI S. S. KATIYAR (<i>Alternate</i>)	Ministry of Defence (DGI)
SHRI SUKESH BOSE	British Paints Ltd, Calcutta
SHRI G. C. DESAI	Goodlass Nerolac Paints Ltd, Bombay
SHRI S. H. DESAI	Garware Paints Ltd, Bombay
DR P. G. CHAUDHARI (<i>Alternate</i>)	Garware Paints Ltd, Bombay
SHRI J. N. GHOSAL	Sturdia Chemicals Ltd, Rishikesh
SHRI H. S. VIJAYANATHAN (<i>Alternate</i>)	Sturdia Chemicals Ltd, Rishikesh
SHRI M. M. GHOSH	Shalimar Paints Ltd, Calcutta
SHRI K. V. KRISHNAN	Colour Chem Ltd, Bombay
SHRI R. M. TILLU (<i>Alternate</i>)	Colour Chem Ltd, Bombay
SHRI V. G. PANCHAMIYA	Kamani Metallic Oxides Pvt Ltd, Bombay
SHRI K. L. RATHI	Sudarshan Chemical Industries Ltd, Pune
SHRI H. J. RATHI (<i>Alternate</i>)	Sudarshan Chemical Industries Ltd, Pune
SHRI P. N. WAGLE	Asian Paints (India) Ltd, Bombay

(Continued on page 13)

IS : 70 - 1980

Indian Standard
SPECIFICATION FOR
CUPROUS OXIDE FOR PAINTS
(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 10 January 1980, after the draft finalized by the Raw Materials for Paint Industry Sectional Committee had been approved by the Chemical Division Council.

0.2 This standard was first published in 1950 and was largely based on the interim co-ordinated draft prepared with the assistance of the Coordinating Subcommittee of the No. 5 Standing Committee on Specifications for Paints and Allied Stores of the General Headquarters, India (now Army Headquarters).

0.3 In this revision additional requirements for combined chlorides and sulphates, metals other than copper and stability of the material have been prescribed. The limit for residue on sieve has been reduced from 2.5 to 0.5 percent by mass.

0.4 In the preparation of this revision assistance has been derived from ASTM Part 28-1976 published by the American Society for Testing and Materials, Philadelphia, USA which is thankfully acknowledged.

0.5 This Indian standard contains clause 4.1 which calls for agreement between the purchaser and the supplier.

0.6 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the results of a test or analysis, shall be rounded off in accordance with IS: 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes requirements and methods of sampling and test for cuprous oxide for paints.

*Rules for rounding off numerical values (*revised*).

IS : 70 - 1980

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given under 2 of IS: 33-1976* shall apply.

3. REQUIREMENTS

3.1 **Composition** — The material, dried as prescribed in 7 of IS : 33-1976*, shall contain not less than 96 percent of cuprous oxide (Cu_2O) by mass when tested as prescribed in Appendix A.

3.2 **Form and Condition** — The material shall be supplied in the form of dry powder; or in such a condition that it can be reduced to the powder form by crushing, without grinding action, under a palette knife.

3.3 The material shall also conform to the requirements prescribed in Table 1.

TABLE 1 REQUIREMENTS FOR CUPROUS OXIDE FOR PAINTS

SL No.	CHARACTERISTIC	REQUIREMENT	METHOD OF TEST, REF TO CL NO. IN	
			Appendix	IS : 33-1976*
(1)	(2)	(3)	(4)	(5)
i)	Volatile matter, percent by mass, <i>Max</i>	0.5	—	7
ii)	Residue on sieve, percent by mass, <i>Max</i>	0.5	—	8
iii)	Oil absorption value	Within ± 5 of the approved sample	—	9
iv)	Colour	Not inferior to the approved sample	—	10
v)	Combined chlorides (calculated as Cl) and sulphates (calculated as SO_4), percent by mass, <i>Max</i>	0.5	B	—
vi)	Metals other than copper, percent by mass, <i>Max</i>	0.5	C	—
vii)	Stability (decrease in total reducing power after stability test), percent by mass, <i>Max</i>	2.0	D	—

*Methods of sampling and test for inorganic pigments and extenders for paints (*second revision*).

IS : 70 - 1980

4. PACKING AND MARKING

4.1 Packing — The material shall be packed in suitable containers as agreed to between the purchaser and the supplier.

4.2 Marking — The containers shall be marked with the following particulars:

- a) Name of the material;
- b) Manufacturer's name and his recognized trade-mark, if any;
- c) Mass of the material;
- d) Batch number or lot number in code or otherwise; and
- e) Month and year of manufacture.

4.2.1 The product may also be marked with Standard mark.

4.2.2 The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

5. SAMPLING

5.1 Representative samples of the material shall be drawn as prescribed in 4 of IS : 33-1976*.

5.2 Criteria for Conformity — A lot shall be declared as conforming to the requirements of this standard if the test results of the composite sample satisfy the requirements prescribed in 3.

6. TEST METHODS

6.1 The colour and oil absorption values of the material shall be determined by comparison with those of the approved sample.

6.2 Tests shall be carried out as prescribed in Appendices A to D and IS : 33-1976*. Reference to the relevant clauses of that standard is given in col 5 of Table 1 and Appendices in 3.1 and col 4 of Table 1.

6.3 Quality of Reagents — Unless specified otherwise, pure chemicals and distilled water (see IS : 1070-1977†) shall be employed in tests.

NOTE — 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of analysis.

*Methods of sampling and test for inorganic pigments and extenders for paints (*second revision*).

†Specification for water for general laboratory use (*second revision*).

IS : 70 - 1980

APPENDIX A

(Clause 3.1)

DETERMINATION OF CUPROUS OXIDE

A-0. GENERAL

A-0.1 Cuprous oxide is estimated by determining the total reducing power by dissolving it in acidulated ferric chloride solution and titrating with standard potassium dichromate solution.

A-0.2 Occasionally, samples of cuprous oxide (especially those of high purity) show some metallic copper, which is generally evident in the residue on sieve test. Metallic copper, if present in a sample, gets involved in the determination of cuprous oxide. In such a case advantage is taken of the fact that cuprous oxide is soluble in cold aqueous ammonia, whereas cupric oxide is but slightly soluble and metallic copper insoluble. The addition of hydrazine sulphate to the reagent tends to reduce any divalent copper entering into solution and prevents interaction of cupric oxide and copper metal. If the extraction is carried out in carbon dioxide atmosphere, the metallic copper-cupric oxide mixture may be separated and the metal determined by solution in acidulated ferric chloride, followed by titration with potassium dichromate.

A-1. APPARATUS

A-1.1 Filter — Place in a tube of the type used for small Gooch crucibles (85 mm in length), a perforated porcelain button, seated at right angles to the stem; build an asbestos pad over it and securely set it by tamping with a glass rod.

A-1.1.1 The filter should be packed in such a manner that the tube may be held in an inverted position without dislodging either the disc or the pad.

A-2. REAGENTS

A-2.1 Extraction Solution — Dissolve 6 g of hydrazine sulphate in 1 litre of liquid ammonia (relative density 0.9).

A-2.2 Acidulated Ferric Chloride — Dissolve 150 g of ferric chloride ($\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$) and 300 ml of hydrochloric acid (relative density 1.16) in 800 ml of air-free water, saturated with carbon dioxide.

A-2.3 Indicator — Suspend 2 g of barium diphenylamine sulphonate and 5 g of sodium sulphate in 50 ml of water, saturated with carbon dioxide, and shake until a uniform suspension of barium sulphate is obtained. Dilute with 50 ml of water and allow to settle. When clear, decant the supernatant liquid through a filter and preserve in a dark bottle.

IS : 70 - 1980

A-2.4 Orthophosphoric Acid — 85 percent by volume.

A-2.5 Standard Potassium Dichromate Solution (0.1 N) — Finely powder about 6 g of potassium dichromate, in a glass or agate mortar, and heat from 30 to 60 minutes, in an air oven at 140 to 150°C. Cool in a desiccator. Dissolve about 4.9 g of the powder, accurately weighed, in water in a 1-litre measuring flask, shake thoroughly and make the solution to 1 000 ml. Allow it to stand overnight.

$$\text{A-2.5.1 Strength of potassium dichromate solution (N)} = \frac{4.9}{M} N$$

where

M = mass in g of potassium dichromate dissolved.

A-2.6 Air-Free Water, Saturated with Carbon Dioxide — Boil water vigorously for several minutes and allow to cool in an atmosphere of carbon dioxide by passing a slow current of the gas continuously through the storage bottle.

A-2.7 Ethyl Alcohol — 95 percent by volume.

A-3. PROCEDURE

A-3.1 In Absence of Free Copper

A-3.1.1 Weigh accurately about 0.25 g of the material, dried as described, under 7 of IS: 33-1976* transfer to a 250-ml glass-stoppered conical flask, add 10 to 15 ml of acidulated ferric chloride solution and a few glass beads. Stopper the flask and rotate gently until the cuprous oxide is completely dissolved, which generally takes place within a few minutes for high grade, finally ground sample. If necessary, warm gently on the water bath to accelerate dissolution. Much heating is not advisable unless the solution is protected from oxidation. When the cuprous oxide is completely dissolved, add 10 ml of orthophosphoric acid and three drops of the indicator and titrate the cold solution at once with 0.1 N potassium dichromate solution until a change of colour from pea-green to intense purple is reached. Run a blank on the reagents used.

A-3.1.2 Calculate the percentage of cuprous oxide using the following relationship:

1 ml of 0.1 N potassium dichromate is equivalent to 0.007 157 g of cuprous oxide.

A-3.2 In Presence of Free Copper

A-3.2.1 Determine the total reducing power as described under **A-3.1**;

*Methods of sampling and test for inorganic pigments and extenders for paints (second revision).

IS : 70 - 1980

and from the percentage of cuprous oxide so ascertained, deduct the cuprous oxide equivalent found under **A-3.2.6**.

A-3.2.2 Weigh accurately about 0.25 g of the material, dried as described under 7 of IS : 33-1976* on a small watch glass and place the watch glass and contents in a dry, wide-mouthed, 250-ml conical flask. Displace the air in the flask with carbon dioxide, the carbon dioxide inlet being kept about 5 cm above the surface of the liquid, and add 10 ml of ethyl alcohol to dissolve any oil present in the sample. Without interrupting the flow of gas, add 150 ml of extraction solution, and break up any lumps of oxide with a stirring rod avoiding violent agitation.

A-3.2.3 The time required for complete solution of all cuprous oxide varies from 1 to 7 minutes, depending upon the amount and character of sample under investigation.

A-3.2.4 When the cuprous oxide has completely dissolved, as evidenced by the total disappearance of red particles, connect the filter to a suction pump and slowly lower into the flask. As soon as the bulk of the solution is removed, rinse the flask with water saturated with carbon dioxide and continue the filtration and washing. Five or six 100 ml portions of wash water will be sufficient to remove all the original extraction solution and dissolved cuprous oxide.

A-3.2.5 Disconnect the filter and push the pad and contents back into the flask with a glass rod. Add 15 ml of acidulated ferric chloride solution and warm the flask to just below boiling point of the solution to dissolve the cupric oxide-copper residue. When all the particles have disappeared, cool the solution to below 40°C and add 10 ml of orthophosphoric acid and 3 drops of the indicator. Titrate the solution with standard potassium dichromate solution until a change in colour from pea-green to intense purple is reached.

A-3.2.6 Calculate the cuprous oxide equivalent of the metallic copper using the following relationship:

1 ml of 0.1 N potassium dichromate is equivalent to 0.007 157 g of cuprous oxide.

APPENDIX B

[Table 1, Item (v)]

DETERMINATION OF COMBINED CHLORIDES AND SULPHATES

B-1. REAGENTS

B-1.1 Barium Chloride Solution — Dissolve 100 g of barium chloride (BaCl₂) in water and dilute to 1 litre.

*Methods of sampling and test for inorganic pigments and extenders for paints (second revision).

IS : 70 - 1990

B-1.2 Silver Nitrate Solution — Dissolve 5 g of silver nitrate (AgNO_3) in 100 ml of water.

B-1.3 Sodium Carbonate Solution— Prepare a saturated solution of sodium carbonate (Na_2CO_3) that is free from both chloride (Cl) and sulphate (SO_4).

B-2. PROCEDURE

B-2.1 Weigh accurately approximately 10 g of the sample, add an excess of nitric acid (relative density 1.42) and heat gently until the sample is decomposed. Dilute with water to approximately 150 ml. Add an excess of sodium carbonate solution and bring to boil. Transfer to a 500-ml volumetric flask and dilute to the mark with water. Allow the precipitate to settle.

B-2.2 Draw off two separate 50-ml aliquots of the clear solution. Make each slightly acidic with nitric acid.

B-2.3 Determination of Chlorides — To one of the 50-ml aliquot add a few drops of silver nitrate solution. If no precipitate forms, report no chlorides present. If a precipitate forms, add slowly an excess of silver nitrate solution. Heat to boiling, after the precipitate has settled, filter through a Gooch crucible and wash with cold water. Dry at 130°C , cool and weigh.

B-2.3.1 Calculation — Calculate the percentage of chlorides (as Cl) as follows:

$$\text{Chlorides, percent by mass} = \frac{M_1 \times 0.247}{(M_2 \times 0.1)} \times 100$$

where

$$M_1 = \text{mass in g of silver chlorides, and}$$

$$M_2 = \text{mass in g of sample used.}$$

B-2.4 Determination of Sulphates — Dilute the second 50-ml aliquot to approximately 200 ml. Add approximately 1 ml of hydrochloric acid (1:1). Heat to boiling and add slowly an excess of barium chloride. Allow the precipitate to settle, filter through a Gooch crucible, and wash. Dry, ignite at full red heat, cool in a desiccator and weigh.

B-2.4.1 Calculation — Calculate the percentage of sulphates (as SO_4), as follows:

$$\text{Sulphates, percent by mass} = \frac{M_1 \times 0.412}{(M_2 \times 0.1)} \times 100$$

where

$$M_1 = \text{mass in g of barium sulphate, and}$$

$$M_2 = \text{mass in g of sample used.}$$

IS : 70 - 1980

APPENDIX G

[Table 1, Item (vi)]

DETERMINATION OF METALS OTHER THAN COPPER

C-1. REAGENTS

C-1.1 Ceric Ammonium Nitrate, Standard Solution (0.1 N) — Mix 54.826 g of ceric ammonium nitrate $[\text{Ce}(\text{NH}_4)_2(\text{NO}_3)_6]$ with 56 ml of sulphuric acid (1 : 1). Dissolve the salt and acid in water, cool to room temperature, and dilute to 1 litre. Standardize this solution against analyzed bright copper foil that has been freed from all oxide coating.

C-1.2 Diphenylamine Indicator — Dissolve 1 g of diphenylamine in 100 ml of sulphuric acid (relative density 1.84).

C-1.3 Potassium Ferricyanide Solution — Dissolve 5 g of potassium ferricyanide $[\text{K}_3\text{Fe}(\text{CN})_6]$ in 100 ml of water. Keep tightly stoppered in a dark bottle.

C-1.4 Potassium Ferrocyanide, Standard Solution — Dissolve 5.0 g of potassium ferrocyanide $[\text{K}_4\text{Fe}(\text{CN})_6 \cdot 3\text{H}_2\text{O}]$ in water and dilute to 1 litre. Standardize with analyzed zinc prior to use.

C-2. PROCEDURE

C-2.1 Weigh accurately 1.0 g of the sample and transfer to a 300 ml electrolytic beaker. Add 10 ml of nitric acid and boil several minutes. Add 10 ml of perchloric acid (HClO_4) (70 percent) and fume for 5 minutes. Cool, dilute to a volume of approximately 150 ml and add 1 ml of nitric acid and 1 g of ammonium sulphate. Electroplate the copper on a rotating platinum electrode at a current of 2A for 2h. Dilute with water and continue the electrolysis for 15 minutes. When the deposition is complete, remove the electrode. Filter the electrolyte, wash with water and acetone. Add 5 ml of sulphuric acid and evaporate just to dryness to remove all perchloric acid and nitric acid. Add approximately 150 ml of water and neutralize with ammonium hydroxide, add 5 ml in excess. Add 10 g of ammonium chloride solution. Boil the solution gently for several minutes and allow the precipitate to settle. Filter through a close-texture paper, and wash the precipitate with 50 ml of hot ammonium chlorides solution (20 g/litre).

C-2.2 Determination of Iron — Dissolve the precipitate from the filter paper with hot hydrochloric acid (1 : 1). Determine iron by the usual procedure of reduction with stannous chloride (SnCl_2) solution, followed by addition of mercuric chloride (HgCl_2) and titration with 0.1N ceric ammonium nitrate solution.

IS : 70 - 1980

C-2.2.1 Calculation— Calculate the percentage of iron as follows:

$$\text{Iron, percent by mass} = [(VN \times 0.056)/M_1] \times 100$$

where

V = volume in ml of ceric ammonium nitrate solution required to titrate the sample,

N = normality of the ceric ammonium nitrate solution, and

M_1 = mass in g of sample used.

C-2.3 Determination of Cobalt and Nickel— Evaporate the filtrate (see C-2.1) to 15 to 20 ml. If the solution is coloured, the presence of nickel or cobalt, or both, may be indicated. If present, they shall be removed before determining zinc, and shall be determined by any standard procedure and reported as percentage of cobalt or nickel, or both.

C-2.4 Determination of Zinc— Neutralize the solution (see C-2.3) with sulphuric acid (1:2) and add 15 ml in excess. Dilute to 300 ml with water. Add 10 drops of potassium ferriocyanide solution and 5 drops of diphenylamine indicator solution. Heat to 75°C and titrate with potassium ferriocyanide solution (1 ml=0.001 g of zinc). A colour change from blue to greenish yellow occurs at the end point.

C-2.4.1 Calculation— Calculate the percentage of zinc as follows:

$$\text{Zinc, percent by mass} = (VN/M) \times 100$$

where

V = volume in ml of potassium ferriocyanide solution required for titration of the sample,

N = zinc equivalent of the potassium ferriocyanide solution,

M_1 = and mass in g of sample used.

C-3. REPORT

C-3.1 Report as percentage of metals other than copper, the total of the percentage of metals determined in accordance with C-2.

APPENDIX D

[Table 4, Item (vii)]

DETERMINATION OF STABILITY

D-1. PROCEDURE

D-1.1 Spread approximately 100 g of the sample on a watch-glass and heat in an oven at a temperature of 40°C and approximately 95 percent relative humidity for a period of 72 h. Remove from the oven. Note any change in colour of the sample. Determine its total reducing power as prescribed in Appendix A.

IS : 70 - 1980

D-1.2 Determine the percentage of moisture on 50 g of the sample remaining from the test described in **D-1.1** using a distillation method.

D-1.3 Calculation — Calculate the percentage of decrease in total reducing power as follows:

$$a = b/(100 - c); d = [(e-a)e] \times 100$$

where

a = total reducing power after, stability test, based on the dry sample,

b = total reducing power as determined in **D-1.1**,

c = percentage of moisture (**D-1.2**),

d = percentage of decrease in total reducing power after stability test, and

e = total reducing power of original sample (see Appendix A).

IS : 70 - 1980

(Continued from page 2)

Panel for Inorganic Pigments, CDC 50 : 1 : 1

<i>Convener</i>	<i>Representing</i>
SHRI G. C. DESAI	Goodlass Nerolac Paints Ltd, Bombay
<i>Members</i>	
SHRI S. BHATTACHARYYA	Alkali and Chemical Corporation of India Ltd, Rishra
SHRI M. L. MALHOTRA <i>(Alternate)</i>	Waldic Limited, Calcutta
SHRI E. G. COWPER	Waldic Limited, Calcutta
SHRI D. V. WITTENBAKER <i>(Alternate)</i>	Waldic Limited, Calcutta
SHRI T. K. S. MANX	Addisons Paints & Chemicals Ltd, Madras
SHRI V. C. PANCHAMIYA	Kamani Metallic Oxides Pvt Ltd, Bombay
SHRI K. L. RATHI	Sudarshan Chemical Industries Ltd, Pune
SHRI H. J. RATHI <i>(Alternate)</i>	Sudarshan Chemical Industries Ltd, Pune
SHRI K. C. SEAL	National Test House, Calcutta
DR V. S. VIJAYAN NAIR	Travancorc Titanium Products Ltd, Trivandrum

BUREAU OF INDIAN STANDARDS

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002
 Telephones: 323 0131, 323 3375, 323 9402
 Fax : 91 11 3234062, 91 11 3239399, 91 11 3239382

Telegrams : Manaksanstha
 (Common to all Offices)

Central Laboratory:

Plot No. 20/9, Sits IV, Sahibabad Industrial Area, SAHIBABAD 201010 Telephone 8-77 00 32

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	323 76 17
*Eastern : 1/14 CIT Scheme VII M, V.I.P. Road, Maniktola, CALCUTTA 700054	337 86 62
Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022	60 38 43
Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113	235 23 15
†Western : Manakalaya, E9 Behind Marol Telephone Exchange, Andheri (East), MUMBAI 400093	832 92 95

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001	550 13 48
‡Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road, BANGALORE 560058	839 49 55
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	55 40 21
Plot No. 62-63, Unit VI, Ganga Nagar, BHUBANESHWAR 751001	40 36 27
Kalaikathir Buildings, 670 Avinashi Road, COIMBATORE 641037	21 01 41
Plot No. 43, Sector 16 A, Mathura Road, FARIDABAD 121001	8-28 88 01
Savitri Complex, 116 G. T. Road, GHAZIABAD 201001	8-71 19 96
53/5 Ward No. 29, R. G. Barua Road, 5th By-lane, GUWAHATI 781003	54 11 37
5-8-58C, L. N. Gupta Marg, Nampally Station Road, HYDERABAD 500001	20 10 83
E-52, Chitaranjan Marg, C-Scheme, JAIPUR 302001	37 29 25
117/418 B, Sarvodaya Nagar, KANPUR 208005	21 68 76
Seth Bhawan, 2nd Floor, Behind Leela Cinema, Naval Kishore Road, LUCKNOW 226001	23 89 23
Patliputra Industrial Estate, PATNA 800013	26 23 06
T. C. No. 14/1421, University P. O. Palayam, THIRUVANANTHAPURAM 695034	6 21 17
NIT Bulking, Second Floor, Gokulpat Market, NAGPUR 440010	52 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	32 36 35
*Sales Office is at 5 Chowringhee Approach, P. O. Princep Street, CALCUTTA 700072	27 10 85
†Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400007	309 65 28
‡Sales Office is at 'F' Block, Unity Building, Narashimaraja Square, BANGALORE 560002	222 39 71