

REDUCED DRG. PREPARED AT CQA(I) DEHRA DUN  
 PREPARED BY :  
 CHECKED BY : *Ms Basak*  
 DATE :  
 FOR CQ  
 D.C:-33209-A, 5818-I, 6479-I.

**TESTS**  
**TEST FOR SOUNDNESS OF COVER**

FIVE SAMPLES PER BATCH OR LOT WILL BE TAKEN AT RANDOM FOR EACH OF THE UNDERMENTIONED TESTS.  
 A) PLACE THE STORE IN A HEATING CHAMBER IN SUCH A MANNER THAT NO MECHANICAL STRESSES ARE APPLIED TO IT. THE STORE SHALL BE MAINTAINED AT A TEMPERATURE OF 75°C FOR A PERIOD OF 24 HOURS.




**PASSING STANDARD**

THE STORE SHOULD NOT EXHIBIT ANY HAIRLINE CRACKS OR DEFORMATION WHEN SUBJECTED TO TEMPERATURE CONDITIONING.

B) PLACE THE STORE IN A COOLING CHAMBER IN SUCH A MANNER THAT NO EXTERNAL MECHANICAL STRESSES ARE APPLIED TO IT. THE STORE SHALL BE MAINTAINED AT 30°C FOR A PERIOD OF 24 HOURS.

**PASSING STANDARD**

THE STORE SHOULD NOT EXHIBIT ANY HAIRLINE CRACKS OR DEFORMATION WHEN SUBJECTED TO TEMPERATURE CONDITIONING



**COVER**

**MATERIAL**  
 FIBER GLASS REINFORCED POLYSTYRENE  
 TO SPEC.IND/ME/802(PROVISIONAL)  
 OLIVE GREEN COLOUR(SHADE No.ISC 220  
 TO IS:5-1978)

**TITLE:-**

AMENDMENTS	CHD	SIG	DATE
D.C:-5818-I-DRG. REDUCED & SEALED IN SUPERSESSION OF IUX-589.			20.1.94
(a) D.C:-6479-I, STENCILLING (EMBOSSED) NOM. AMENDED.			5.5.2000

FOR EXPLANATION OF DIMENSIONING ETC, SEE CQA (I) GUIDE No 001-1992. THIRD ANGLE PROJECTION DIMENSIONS ARE IN mm	DRN	APPROVED
	TCD	FOR <i>W</i>
	CHD	CONTROLLER
	CHD	CQA (I) D.DUN
MATERIAL & SPEC:- AS ABOVE	USED	
	ON	
	BASED ON	TUX 589
FINISH & SPEC:-	CAT/PT No.	
	DRG No.	CQA (I) 408/3
	SCALE	SI OF