

Date: 05.10.2019

Amendment No. 1 to Specification No.1201909/001 dt. 10.09.2019

1. Under Heading Specification b) Physical, Point No (iii)

FOR : GSM $240 \pm 2.5 \%$

READ: GSM $240 \pm 4.5 \%$

2. Under heading d) Ballistic, Point No. (i)

FOR : Existing

READ: Multiple layers of fabric to a maximum areal density of 4.0 kg/m^2 , when subjected to ballistic testing shall be able to withstand 9mm FMJ RN Bullet (7.4 to 8.2 gms weight and $430 \pm 15 \text{ m/s}$ velocity) fired through 9mm Sub Machine Gun (such as Sten Machine, MP-5 Carbine, any other variant) at a distance of 5 meter as per NIJ 0101.06 standard threat level IIIA.


Jt.GM/ODC