




**TECHNICAL PARTICULARS FOR RUBBER BAND, 13 MM WIDTH, 150 MM CIRCUMFERENCE**

| Sl. No. | Parameters                  | Specified value | Test Method              |
|---------|-----------------------------|-----------------|--------------------------|
| 1       | Circumference, mm           | 150±5           | IS: 1954                 |
| 2       | Width, mm                   | 13±0.1          | IS: 1954                 |
| 3       | Thickness, mm               | 1.3±0.1         | IS: 7702                 |
| 4       | Breaking Load, N, min       | 330             | IS: 1969                 |
| 5       | Elongation at break, %, min | 500             | IS: 1969                 |
| 6       | Material                    | Hypalon Rubber  | Pyrolusate colour method |

  
Gaurav Singh  
Scientist 'E', DH, TG(TE)

  
Prasanta Kumar Mallik  
Scientist 'D'

  
S. K. Pal  
Scientist 'G', GD, TG(TE)