

Technical Particulars for Tape Nylon Black Stretch, 26 mm, 1050 N BS

Sl. No.	Parameters	Specified Values	Test Method
1	Width, mm	26±1	IS: 1954
2	Thickness, mm, max (at 200 g/cm ² Pressure)	0.90	IS: 7702
3	Mass, g/m, max	6.6	IS: 4727
4	Breaking Strength, N, min	1050	IS: 1969
5	Extension at break, %, min	20	IS: 1969
6	Suggested Constructional Parameters i) Linear Density of Yarn, Tex [tolerance: ±10%] Warp Weft ii) No. of ends in full width iii) Picks/dm	24.5x1 12.5x1 178+1 ILT 360-400	IS: 3442 IS: 1963
7	Weave	Plain, 2 picks/shed	Visual
8	Material	Black, High Tenacity, Multifilament, Nylon 6 / Nylon 66 Crimp Yarn	IS: 5762
9	Colour Fastness to Light	4 or better	IS: 686 or IS: 2454
10	Colour Fastness to Washing	No colour bleeding on white cotton/white wool	IS: 764
11	pH Value	5.5 – 8.5	IS: 1390 Cold Method

Note: These technical particulars are the revision of existing technical particulars w.r.t constructional parameters. These may undergo certain amendments in further supplies, if required.

21/06/19 12:18
Gaurav Singh
Scientist 'E'
DH, TG(TE)

Prasanta Kumar Mallik
Scientist 'D'

S. K. Pal
Scientist 'G'
GD, TG(TE)