

FOUNDRY SECTION

SUB:SPECIFICATION FOR QUARTZITE SILICA PARTICLES REG:


CHEMICAL COMPOSITION: As per IS:1987-1974

---

GRADE	:	A
Silica	:	Over 98 %
Alumina	:	1.0 % Max.
Iron Oxide	:	1.0 % Max.
Calcium & Magnesium Oxide	:	1.0 % Max.
Alkalies	:	0.50 % Max.

---

The firm shall submit test certificate from NABL accredited lab / National or International Standards certified labs certification conforming to the above specification.

  
AWM/FDY

  
HOS/FDY