5. COMBUSTIBLE CARTRIDGE COMPONENTS FOR M-91 (CASE, PROPELLANT RETAINING DEVICE(PRD) & IGNITER TUBE (IT))

1. ACCEPTANCE CRITERIA

1.1 CHEMICAL COMPOSITION OF CCC (CASE, PRD & IT) FOR M-91

Ingredients	Composition		
	Case	PRD	IT .
NC (Gun cotton), %	71.0 - 79.0	71.0 - 79.0	71.0 - 79.0
Colour Hue	132 - 152	132 – 152	132 - 152
Ethyl Centralite, %	1.8 - 3.0	1.8 - 3.0	1.8 - 3.0

1.2 PHYSICAL PROPERTIES (CASE, PRD & IT) FOR M-91

* T	Specified Value			
Test Parameters	Case	PRD*	IT	
Volatile Matter %	≤ 4.0	` ≤ 4.0	≤ 4.0	
Methyl Violet at 134.5°C (in Minutes)				
Complete discolouration to pink	Not less than 40	Not less than 40	Not less than 40	
Emission of brown fumes	Not less than 60	Not less than 60	Not less than 60	

1.3 DIMENSIONS (CASE, PRD & IT) FOR M-91

Channadaniation	Specification Limit			
Characteristics	Case PRD		IT	
Dimensions #	As per drawing No. OFN/BMCS/M-91/CCC	1 0	As per drawing No. OFN/BMCS/M-9 1 /M-9 2 /IT	

Critical Dimensions to be checked as per Gauge Schedule

1.4 Weight

Characteristics		Specification Limit	
Characteristics	Case	PRD	IT
Weight (g)	213.5 -248.5	37-43	31-35

1.5 Inspecting Authority: GM / O F Nalanda or his authorised representative 1.6 Accepting Authority: GM / O F Nalanda or his authorised representative

Youdan

W_