

Technical Particulars for Tape Cotton 30 mm, 340 N BS, Undyed

Sl. No.	Parameters	Specified Values	Test Method
1	Width, mm	30±1	IS: 1954
2	Thickness, mm, max (at 200 g/cm ² Pressure)	0.44	IS: 7702
3	Mass, g/m, max	5.5	IS: 1964
4	Breaking Strength, N, min	340	IS: 1969
5	Linear Density of Yarn, Tex [tolerance: ±10%] Warp Weft	19.7 x 2 9.8 x 2	IS: 3442
6	No. of ends in full width	86 + 1 ILT	IS: 1963
7	Picks/cm	21±2	
8	Weave	Plain, 2 ends working as one, 2 picks/shed	Visual
9	Material	Cotton	IS: 667

Note: These technical particulars are tentative and these may undergo certain amendments during development, if required.



Dev Kishan Bairwa
Scientist 'B'



Prasanta Kumar Mallik
Scientist 'D'



Gaurav Singh
Scientist 'F'
DII, TG(TE)



S. K. Pal
Scientist 'G'
GD, TG(TE)