


Technical Particulars for Tape Nylon, Tubular, Braided, 20 mm, 5680 N BS

Sl. No.	Parameters	Specified Values	Test Method
1	Width, mm	20±1	IS: 1954
2	Thickness, mm, max (at 200 g/cm ² Pressure)	2.0	IS: 7702
3	Mass, g/m, max	20.5	IS: 4727
4	Breaking Strength, N, min	5680	IS: 1969
5	Extension at break, %, min	20	IS: 1969
6	Linear Density of Yarn, Tex x Ply [tolerance (-) 3 to (+) 8%]	23.3 x 3	IS: 3442
7	Constructional Parameters a. No. of spindles b. No. of ends/spindle c. Total no. of ends	64 3 192	IS: 7071 Part – I to III
8	Plaits/dm	38±4	IS: 4227 Annex. 'D'
9	Yarn Twist per meter, TPM	Single: 300±10% Ply: 200±10%	IS: 832
10	Construction	Braided, Coreless	Visual
11	Material	Bright, High Tenacity, Multifilament, Nylon 6/Nylon 66 Yarn	IS: 5762


Note: These technical particulars are tentative and these may undergo certain amendments during development, if required.




Dev Kishan Bairwa
Scientist 'B'



Prasanta Kumar Mallik
Scientist 'D'



Gaurav Singh
Scientist 'F'
DH, TG(TE)



S. K. Pal
Scientist 'G'
GD, TG(TE)