

क्र. मं०/१०७
दिनांक 14/07/14
मंत्रालय द्वारा अनुमोदित
Approved by Ministry of Defence
Vide letter No. 1000100 dated

समन्वय मानकी
के अनुसार रक्षा
S.S.C.



रक्षा मंत्रालय (संयोजन)
Asstt. Director (T.C.I.)
राज्यीय रक्षा निर्देशक
Directorate of Standardisation
रक्षा मंत्रालय, नई दिल्ली
Min of Defence, New Delhi

रक्षा मंत्रालय
MINISTRY OF DEFENCE

ज्वाइंट सर्विस स्पेसिफिकेशन
JOINT SERVICES SPECIFICATION

ON

TAPE, NYLON, DYED / UNDYED
(DS cat No.8315 - 000 257 to 000 268)

मानकीकरण निदेशालय
रक्षा उत्पादन विभाग
रक्षा मंत्रालय

'एच' - ब्लॉक, निर्माण भवन डाकघर
नई दिल्ली - 110 011

DIRECTORATE OF STANDARDISATION
DEPARTMENT OF DEFENCE PRODUCTION
MINISTRY OF DEFENCE
'H' - BLOCK, NIRMAN BHAVAN, P.O.
NEW DELHI - 110 011

LIST OF MEMBERS ASSOCIATED WITH FORMULATION OF THIS STANDARD

1. The revision of this Joint Services Specification has been approved by Shri Sanjeev Kapur-Addl DGQA (S), Chairman, Stores Standardisation Sub - Committee.
2. The following members have been associated in preparing the document :

Sl. No.	Name and Designation	Organisation
(a)	Wg Cdr.SKS Gosain, JDQAS (S & C)	DQAS (Aero) / Air HQ
(b)	S. Chakraborty, SSO - I	CQA (T & C)
(c)	Dr. S. K. Pandey, SSO - I	CQA (M)
(d)	Shri R S Diwakar, JAG (NFSG)	CQA (PP)
(e)	Shri D K Pujari, SSO - I	CQA (GS)
(f)	Cdr. Naveen Kumar (IN)	DQA (N)
(g)	Shri Jarnail Singh, Dy Director	DGAQA
(h)	Sh. Suraj Raj, SSO - II	DGAQA
(j)	Maj. S. Bansal, DD OS (PII)	MGO / CP Cell / OS Dte.
(k)	Shri Pinaki Sengupta, Dy Dir	MGO Br / EM / GS & C
(l)	Wg Cdr Chaturvedi, Deputy Director	Dte of Stores / Air HQ
(m)	Lt. Col Pankaj Bishr, Jt Dir EM (Std) (Army Std Cell)	MGO / EM / Std
(n)	Shri BL Jatav - NSO	NHQ / DCV
(o)	Cdr R Venkatesan, JDME	NHQ / DOS (E)
(p)	Dr. D N Tripathi, Sc. 'F'	DMSRDE
(q)	Shri S B Yadav, Sc. 'F'	DMSRDE
(r)	Cdr. Manish Singh (JDLS)	JDLS
(s)	Shri S.K. Bandyopadhyay, JGM	OEF, Kanpur
(t)	Shri Ajay Satija, AE (QA)	DSC, Kanpur
(u)	Lt. Col. Parveen Deo	Secy, SSSC.

W 200

17/5/15
17/07/15
SSC
Ministry of Defence

RAKSHA MANTRALAYA / MINISTRY OF DEFENCE
MANAKIKARAN NIDESHALAYA / DTE OF STANDARDISATION
(STORES STANDARDISATION SUB-COMMITTEE)

8/09
Ministry of Defence, New Delhi

Amendment - 1 April 2015
The following Amendments are approved:

No. of sheet : (One)
Authority : As shown in col.4

JSS& Year	Nomenclature	Details of Amendment	Authority for Amendment								
1 ISS 8315-06:2014 (Revision No.2)	2 Tape, Nylon, Dyed /Undyed (DS Cat No.8315-000 257 to 000 268)	3 (1) Page No.3, Sub Clause 2.1 at Srl. No. (a), Column No. (3) Under the heading Related Specification as under:- <table border="1"> <tr> <td>FOR</td> <td>(a) Test for Colour Fastness Part C10 :Colour Fastness to washing with soap or soap and soda</td> </tr> <tr> <td>READ</td> <td>Methods for determination of Colour Fastness of textile materials to washing. Test No.C (3)</td> </tr> </table> (2) Page No 6, Sub Clause 9.1 under the heading Quality Assurance at Srl No. (m) (ii) Column (4) under the heading methods (Refer to) : <table border="1"> <tr> <td>FOR</td> <td>(m) IS/ISO 105-C10:2006</td> </tr> <tr> <td>READ</td> <td>(ii) IS/ISO 105- C10:2006 Test No. C (3)</td> </tr> </table>	FOR	(a) Test for Colour Fastness Part C10 :Colour Fastness to washing with soap or soap and soda	READ	Methods for determination of Colour Fastness of textile materials to washing. Test No.C (3)	FOR	(m) IS/ISO 105-C10:2006	READ	(ii) IS/ISO 105- C10:2006 Test No. C (3)	4 CQA(T&C) Kanpur G/8104/Adopted JSS/TC-3 dt 13/10/14
FOR	(a) Test for Colour Fastness Part C10 :Colour Fastness to washing with soap or soap and soda										
READ	Methods for determination of Colour Fastness of textile materials to washing. Test No.C (3)										
FOR	(m) IS/ISO 105-C10:2006										
READ	(ii) IS/ISO 105- C10:2006 Test No. C (3)										

RECORD OF AMENDMENTS

Amendment		Amendment pertains to: Sl. No. / Para No. / Column No.	Authority	Amended by	Signature & Date
No.	Date			Name & Appointment (IN BLOCK LETTERS)	

श्री अरुण सिंह
श्री अरुण सिंह (श्री अरुण सिंह)
श्री अरुण सिंह (श्री अरुण सिंह)
श्री अरुण सिंह (श्री अरुण सिंह)
श्री अरुण सिंह (श्री अरुण सिंह)

Sl. No.	CONTENTS	Page No.
0.	FOREWORD	1 - 2
1.	SCOPE	3
2.	RELATED SPECIFICATIONS	3 - 4
3.	STANDARD PATTERN	5
4.	MATERIAL	5
5.	MANUFACTURE	5
6.	DIMENSIONS AND OTHER DETAILS	5
7.	WORKMANSHIP AND FINISH	5
8.	MARKING	5
9.	QUALITY ASSURANCE	6
10.	PRE - INSPECTION OF STORES / CONSIGNMENT	7
11.	SAMPLING	7 - 8
12.	CRITERIA FOR CONFORMITY	8
13.	WARRANTY	9
14.	PACKAGING	9 - 10
15.	DEFENCE STORES CATALOGUE NUMBERS	11
16.	SUGGESTIONS FOR IMPROVEMENT	11
17.	APPENDIX 'A & B'	12 - 13

0. **FOREWORD**

0.1 This specification has been prepared by the Stores Standardisation Sub Committee on the authority of Standardisation Committee, Ministry of Defence.

0.2 This specification has been approved by the Ministry of Defence and is mandatory for use by the Defence Services.

0.3 (a) This JSS was prepared in the year Dec 1981.

(b) First revision was done in the year 1998 & Reaffirmed - 2008.

(c) This specification is a revision of JSS 8315 - 06 : 1998 (Revision No.1), Reaffirmed - 2008 and supersedes the same.

0.4 This specification would be used to Guide, Design, Manufacture, Quality Assurance and Procurement of the item:

0.5 Quality Assurance Authority for the item covered by this specification is CQA (T & C), Kanpur and DQAS (Aero), New Delhi for Army and Air Force respectively. Enquiries regarding technical parameters shall be addressed to the Quality Assurance Authority, while other enquiries shall be referred to :

The Director,
Directorate of Standardisation,
Ministry of Defence,
'H' Block, Nirman Bhavan PO,
New Delhi - 110 011

0.6 Non - registered users can obtain the following on payment :

(a) **Copies of IS from :**

Bureau of Indian Standards,
Manak Bhavan,
9, Bahadur Shah Zafar Marg,
New Delhi - 110 002

or
their regional / branch offices

(b) **Copies of JSS / JSG from :**

The Director,
Directorate of Standardisation,
Standardisation Documents Centre
Ministry of Defence
Room No.05, 'J' Block, Nirman Bhavan PO,
New Delhi - 110 011

0.7 Indian Standard (IS) specifications are available free of cost for registered users on :

Directorate of Standardisation Website
www.ddpdos.gov.in
for registration visit our website.

0.8 This specification holds good only for the supply order for which it is issued.

0.9 Directorate of Standardisation Website. All the approved JSSs / JSGs are available on the Directorate of Standardisation Website **www.ddpdos.gov.in** Defence organisations desirous of accessing a copy of this document are requested to approach the Directorate of Standardisation for obtaining user id / password to access the website.

1. **SCOPE**

1.1. This specification covers the requirements of Tape, Nylon, Dyed / Undyed in various sizes used in the manufacture of personnel parachutes and other aerial delivery equipments.

2. **RELATED SPECIFICATIONS**

2.1. Reference is made in this specification to :-

Sl. No.	Specification / Document No.	Nomenclature
(a)	IS / ISO 105 - C 10 : 2006	Textiles - Tests for Colour Fastness : Part C10 : Colour Fastness to Washing with Soap or Soap and Soda
(b)	IS 832 : 1985 (First Revision) Reaffirmed - 2010 Amd - 2	Methods for Determination of Twist in Yarn
(c)	IS 1315 : 1977 (First Revision) Reaffirmed - 2010 Amd - 1	Method for determination of linear density of yarns spun on cotton system
(d)	IS 1390 : 1983 (First Revision) Reaffirmed - 2009	Methods for determination of pH value of aqueous extracts of textile materials
(e)	IS 1398 : 1982 (Second Revision) Reaffirmed - 2009 Amd - 1	Specification for Packing Paper Water Proof, Bitumen - Laminated
(f)	IS 1912 : 1984 (Second Revision) Reaffirmed - 2011 Amd - 1	Specification for Country Jute Twine
(g)	IS 1954 : 1990 (Second Revision) Reaffirmed - 2007	Determination of Length and Width of Woven Fabrics - Methods

Sl. No.	Specification / Document No.	Nomenclature
(j)	IS 1963 : 2004 (Second Revision) Reaffirmed - 2008	Methods for Determination of Threads per Unit Length in Woven Fabrics
(k)	IS 1964 : 2001 (Second Revision) Reaffirmed - 2010	Textiles - Methods for determination of Mass per unit length and mass per unit area of fabrics
(l)	IS 1969 : 1985 (Second Revision) Reaffirmed - 2010 Amd - 1	Methods for Determination of Breaking load and Elongation of Woven Textile Fabrics
(m)	IS 2454 : 1985 (First Revision) Reaffirmed - 2013 Amd - 1	Methods for determination of colour fastness of textile materials to artificial light (xenon lamp)
(n)	IS 2500 - Part 1 : 2000 (Third Revision) Reaffirmed - 2011 Amd - 1	Sampling Procedure for Inspection by Attributes : Part 1 : Sampling schemes Indexed by Acceptance Quality Limit (AQL) for Lot - by - Lot Inspection
(o)	IS 2508 : 1984 (Second Revision) Reaffirmed - 2008 Amd - 3	Specification for Low Density polyethylene Films
(p)	IS 2771 : Part 1 : 1990 (Second Revision) Reaffirmed - 2008 Amd - 3	Corrugated Fibreboard Boxes - Specification : Part 1 : General Requirements
(q)	IS 4905 : 1968 Reaffirmed - 2011 Amd - 1	Methods for random sampling
(r)	IS 10106 : Part 3 / Sec 1 : 1984 Reaffirmed - 2009	Packaging code : Part 3 : Ancillary materials : Section 1 : Cushioning materials
(s)	JSS 8135 - 10 : 2004 (Revision No. 1) Reaffirmed - 2011 Amd - 1	Polypropylene Strapping, 12 mm wide

उद्योगिक निदेशक (निष्काशक)
Asstt. Director (T.O.)
प्रादेशिक सूत्र विभाग
Directorate of Standards & Quality
सूत्र विभाग, कानपुर
Asstt. Dir. (T.O.), Kanpur

3. **STANDARD PATTERN**

3.1 The Standard pattern of Tape, Nylon, Dyed / Undyed held in the custody of the Controllorate of Quality Assurance (Textiles & Clothing), Post Box No. 294, Kanpur - 208 004 shall constitute the standard as regards any particulars or properties not noted or defined in this specification.

4. **MATERIAL**

4.1 The basic material of yarn shall be Nylon type '6' or '66'. The yarn for both wrap and weft shall be bright, multifilament of high tenacity and of 23 tex.

5. **MANUFACTURE**

5.1 The single and folded yarns shall be evenly twisted. The tape shall be evenly woven under suitable tension. The edges of the tape shall be firm and regular.

5.2 The dyed tapes shall be manufactured either by use of dyed yarn in the weaving or by dyeing the tapes. The yarn or tapes shall be dyed with disperse or acid type dye. Metallised or chromic dyes shall not be used.

5.3 The yarns used for both wrap and weft shall be twisted together (plied) in one operation.

6. **DIMENSIONS AND OTHER DETAILS**

6.1 Tape, Nylon, dyed / undyed shall conform to the essential particulars given in Appendix 'A'.

7. **WORKMANSHIP AND FINISH**

7.1 The Tape shall be free from weaving defects. When laid on a flat even surface, the tape shall be in a straight line without any application of tension.

8. **MARKING**

8.1 Each roll shall be suitably attached with a label. The label shall legibly and indelibly marked with the manufacture's name, initials or recognised trade mark, year of manufacture, length of roll, nomenclature and the DS Cat Number of the store.

9. **QUALITY ASSURANCE**

9.1 Examination of the samples taken from any portion of a consignment shall show that the tapes conform to the following requirements when tested as per method mentioned against each :

Sl. No.	Tests	Requirements	Methods(Refer to)
(1)	(2)	(3)	(4)
(a)	Length	100 m or as ordered	IS 1954 : 1990
(b)	Width	As per Col. 2 of Appendix 'A'	IS 1954 : 1990
(c)	Thickness	As per Col.3 of Appendix A	Appendix 'B'
(d)	Mass in 'g' per 100 m	As per Col.8 of Appendix 'A'	IS 1964 : 2001
(e)	Picks per dm	As per Col.5 of Appendix 'A'	IS 1963 : 2004
(f)	Total No. of end in full width, Min	As per Col.4 of Appendix 'A'	IS 1963 : 2004
(g)	No. of folds of yarn Warp Weft	As per Col.6 of Appendix 'A' As per Col.7 of Appendix 'A'	IS 1315 : 1977
(h)	Turns per metre	100	IS 832 : 1985
(j)	Breaking load (on full width x 20 cm)	As per Col.9 of Appendix 'A'	IS 1969 : 1985
(k)	Elongation at break, percent. Min	18	IS 1969 : 1985
(l)	pH value of aqueous extract	6.0 to 8.5	IS 1390 : 1983 (cold method)
(m)	Dye fastness (i) To light (ii) To washing	Class 5 or better Rating 4 or better	IS 2454 : 1985 IS / ISO 105 - C 10 : 2006
(n)	Linear density of yarn	As per Col.12 & 13 of Appendix 'A'	IS 1315 : 1977

SAMPLING TABLE

As per Sampling plan AQL 4 % as per table I for visual inspection (Based on General Inspection level II) and table II for laboratory testing (Based on and S - 3) as per IS 2500 - Part I : 2000.

TABLE - I				TABLE - II
Sl. No.	Lot Size In roll's	No. of samples to be drawn by sampling officer for visual Examination (General Inspection Level II)		Sub Sample Size (No. of rolls to selected for lab)
		Sample Size (n)	Acceptance Number (Ac)	
(1)	(2)	(3)	(4)	(5)
(a)	Up to 25	5	0	3
(b)	26 to 50	8	1	3
(c)	51 to 90	13	1	5
(d)	91 to 150	20	2	5
(e)	151 to 280	32	3	8
(f)	281 to 500	50	5	8
(g)	501 to 1200	80	7	13

- NOTE :**
- (1) Sampling shall be done randomly as per IS 4905 : 1968.
 - (2) Inspection level S - 3 for laboratory tests.
 - (3) The Rejection number (Re) will always be one more than acceptance Number (Ac).
 - (4) When the Sample size equals or exceeds lot-size 100 % inspection / non - destructive testing with zero acceptance number shall be carried out.

12. CRITERIA FOR CONFORMITY

12.1 All the sample units drawn shall be tested / examined to the relevant specification requirement. If all the sample units are found to conform to the requirements of this specification, the supply would be considered to be in conformity, otherwise not.

13. WARRANTY

13.1 Except as otherwise provided in the invitation to the tender, the contractor / seller hereby declares that the goods / stores, articles sold / supplied to the purchase under this contract shall be of the best quality and workmanship and new in all respect and shall be strictly in accordance with the specification and particulars contained / mentioned in the contract. The contractor / seller hereby guarantees that the said goods / stores / articles would continue to conform to the description and quality aforesaid for a period of 12 months from the date of delivery of the said goods / stores / articles to the purchaser or 15 months from the date of shipment / dispatch from the contractor work whichever is earlier and that notwithstanding the facts that the purchaser (QAO) may have inspected and / or approved the said goods / Stores / articles. If during the aforesaid period of 12 / 15 months the said goods / stores / articles be discovered not to be conform to the description and quality aforesaid or not giving satisfactory performance or have deteriorated and the decision of the purchaser in that behalf shall be final and binding on the contractor / seller to rectify / replace by acceptable goods / stores / articles or such portion or portions thereof as is found to be defective by the purchaser within a reasonable period not exceeding 03 months or as may be allowed by purchaser in his discretion on the application made thereof by the contractor / seller and in such an event the above mentioned warranty period shall apply to the goods / stores / articles rectified / replaced from the date of rectification / replacement thereof, otherwise the contractor / seller shall pay to the purchaser such compensations as determined by the purchaser as may arise by reason of the break of the warranty herein contained.

14. PACKAGING

14.1 The following materials shall be used for packing of Tape, Nylon dyed / undyed :

Sl. No.	Materials	Conforming to
(a)	Polyethylene film 0.04 mm thick	IS 2508 : 1984
(b)	Twine, jute, 3 ply	IS 1912 : 1984
(c)	Packing paper, waterproof bitumen laminated using Kraft paper having substance 60 g / m ² , Min)	IS 1398 : 1982 (Type I)
(d)	Triple walled corrugated fibreboard boxes(outer liners shall be laminated with polyethylene to provide waterproofness)	IS 2771 : Part 1 : 1990
(e)	Polypropylene Strapping, 12 mm wide	JSS 8135 - 10 : 2004
(f)	Cushioning material	IS 10106 : Part 3 / Sec 1 : 1984

14.2 Method

14.2.1 The appropriate number of rolls shall be arranged in cylindrical bundles and secured by 3 ply jute twine to form a unit pack. Suitable number of such packs shall be arranged and wrapped with polyethylene film. Alternatively one layer of packing paper, waterproof, bitumen laminated can be used in emergent condition when polyethylene film is not available. It shall then be placed in a triple walled corrugated fibreboard box duly lined with packing paper, waterproof, bitumen laminated.

14.2.2 Empty spaces, if any, shall be filled with suitable cushioning material to prevent any movement of the contents inside the box. The boxes shall then be strapped by polypropylene strapping at two places. The strapping shall be at one sixth distance from each end of the box and round the body of the box.

14.2.3 The gross mass of the package shall not exceed 40 kg.

14.3 Marking

14.3.1 Before despatch, each box shall be legibly marked by stencil, showing the following details:

- (a) DS Cat number and nomenclature of the store.
- (b) Quantity packed in the box.
- (c) Lot and serial number of the box.
- (d) Month and year of packing.
- (e) Gross mass of the box in kg.
- (f) Name and address of the consignee.
- (g) Name / Trade mark of the supplier.
- (h) Inspection Note number and date.

15. **DEFENCE STORES CATALOGUE NUMBERS**

15.1 Tape, Nylon, dyed / undyed covered by this specification shall bear the following DS Cat numbers :

Sl. No.	DS Cat No.	Nomenclature Tape, Nylon, Undyed
(a)	8315 - 000 257	14 mm
(b)	8315 - 000 258	19 mm
(c)	8315 - 000 259	25 mm
(d)	8315 - 000 260	32 mm
(e)	8315 - 000 261	38 mm
(f)	8315 - 000 262	44 mm
		Nomenclature Tape, Nylon, Dyed
(g)	8315 - 000 263	14 mm
(h)	8315 - 000 264	19 mm
(j)	8315 - 000 265	25 mm
(k)	8315 - 000 266	32 mm
(l)	8315 - 000 267	38 mm
(m)	8315 - 000 268	44 mm

16. **SUGGESTIONS FOR IMPROVEMENT**

16.1 Any suggestion for improvement in this document may be forwarded to :

The Director,
Directorate of Standardisation,
Ministry of Defence,
'H' Block, Nirman Bhawan PO,
New Delhi - 110 011.

JSS 8315 - 06 : 2014
(Revision No. 2)

Handwritten signature and text in Chinese:
 廣東省紡織科學院 (廣東省紡織科學院)
 Guangdong Textile Science Academy (G.T.S.A.)
 廣東省紡織科學院 紡織研究所
 Guangdong Textile Science Academy Textile Research Institute
 廣東省紡織科學院 紡織研究所
 Guangdong Textile Science Academy Textile Research Institute
 廣東省紡織科學院 紡織研究所
 Guangdong Textile Science Academy Textile Research Institute

APPENDIX 'A'

Variety No.	Width in (mm)	Thickness in mm (under a pressure of 210 g/cm ²)	Ends in full width (min)	Picks per dm	Number of folds of yarn		Mass per 100 m in g (max)	Breaking load (full width x 20 cm)	Percentage elongation at break (min)	Weave	Linear density of yarn (Tex)	
					Wrap	Weft					Wrap	Weft
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)
1.	14 + 1	0.64 to 1.0	92	134	2	4	870	2260	18	*	23	23
2.	19 + 1 - 0	0.5 to 0.8	150	148	1	2	620	1900	18	@	23	23
3.	25 + 1 - 0	- do -	75	134	4	2	1120	3960	18	*	23	23
4.	32 + 1 - 0	- do -	94	134	4	2	1400	4970	18	*	23	23
5.	38 + 1.5 - 0	- do -	112	134	4	2	1675	5940	18	*	23	23
6.	44 + 1.5 - 0	- do -	132	134	4	2	1955	6920	18	*	23	23

* 2 up and 2 down herringbone twill with one reversal of twill in the centre.

@ 2 up and 2 down herringbone twill with one reversal of twill at the centre and 2 end woven as one

NOTE : Breaking Load - No individual reading should be less than specified.

बहुमंडल विद्ययालय, दिल्ली
Multi Director (T.C.)
बहुमंडलीय विद्यालय
Bimandlayee of Standardization
बहुमंडलीय विद्यालय, दिल्ली
Multi Director (T.C.)

APPENDIX 'B'

B. METHOD FOR DETERMINATION OF THICKNESS

B.1 Prior to test, the test specimens shall be conditioned in a standard atmosphere of 65 ± 2 percent relative humidity and $27 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$ temperature for at least 24 hours. Take a test specimen and determine the thickness under a pressure of 210 g / cm^2 at different places and calculate the average of these results.

NOTE : Breaking Load - No individual reading should be less than specified.